

Test Report

Report Number:
258637-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 258637
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Nalia. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 27 May 2024.

Period: The test took place from 28 May 2024 to 20 June 2024.

Method: The test methods used are referenced in connection with the results. See page 5.

Test results: The results are shown from page 5 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.







Charlotte Fischer
Senior Consultant



DANAK
TEST Reg.no. 2



Samples

Sample mark	Description	Photo
100	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
120	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
130	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
140	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
160	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
170	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	







Samples (*continued*)

Sample mark	Description	Photo
220	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
240	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
150	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
250	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
270	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
380	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	



Samples (*continued*)

Sample mark	Description	Photo
430	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
580	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
630	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	
990	Sample of upholstery fabric Designated: Nalia Composition: 39% viscose, 28,5% cotton, 14% lin, 9% acrylic, 7% polyamide, 2,5% polyester	



Results

Test of Samples of upholstery fabric designated: Nalia

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
100	6-7
120	6-7
130	6-7
140	6-7
160	6-7
170	6
220	6-7
240	6-7
150	6-7
250	6
270	6
380	6-7
430	6-7
580	6-7
630	6-7
990	6-7
