

Test Report

Report Number:
256996-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 256996
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Sample of upholstery fabric designated: Zade. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 13 May 2024.

Period: The test took place from 14 May 2024 to 14 June 2024.

Method: The test methods used are referenced in connection with the results. See page 5.

Test results: The results are shown from page 5 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.







Charlotte Fischer
Senior Consultant



DANAK
TEST Reg.no. 2




Samples

Sample mark	Description	Photo
570 Red	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
570 Black	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
120 Beige	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
120 Dark beige	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
340 Beige	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
340 Dark brown	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	







Samples (*continued*)

Sample mark	Description	Photo
960 Yellow	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
960 Green	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
280 Beige	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
280 Dark brown	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
660 Pink	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
660 Bordeaux	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	



Samples (*continued*)

Sample mark	Description	Photo
370 Light brown	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
370 Dark brown	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
930 White	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	
930 Green	Sample of upholstery fabric Designated: Zade Composition: 25% cotton, 58% viscose, 19% polyester	



Results

Test of Sample of upholstery fabric designated: Zade

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
570 Red	6-7
570 Black	6-7
120 Beige	6-7
120 Dark beige	6
340 Beige	6-7
340 Dark brown	6-7
960 Yellow	6
960 Green	6-7
280 Beige	6-7
280 Dark brown	6-7
660 Pink	6-7
660 Bordeaux	6-7
370 Light brown	6
370 Dark brown	7
930 White	6-7
930 Green	6-7
