

kvadrat

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft Denmark
T +45 89 53 18 66 F +45 89 53 18 00
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

Fastness to rubbing ISO 105-X12

Re-wool 2

Colour number	Dry condition	Wet Condition
108	5	5
128	4-5	4-5
147	5	4-5
158	4-5	4-5
198 *	4-5	4
218	4-5	4-5
347	4-5	4-5
377	4-5	4-5
397 *	4-5	4-5
447	4-5	4-5
558	4-5	4
568	4-5	4-5
577 *	4-5	4-5
648	4-5	4-5
657	4-5	4-5
687	4-5	4-5
718	4-5	4-5
767 *	4-5	4-5
787	4-5	4-5
797 *	4-5	5
858	5	4-5
868	5	4-5
967 *	4-5	5
977	4-5	4-5
987	4-5	4-5

*TZU report AZL 25/0029-01, 09.01.2025
Internal test 03.03.2023



TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0029-01

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: **Fabric Re-wool 2**
(according to the customer order) Fibre composition: 45 % recycled wool / 45 % new wool, worsted / 10 % nylon
Item number: 7833
Colours: 0198, 0397, 0577, 0767, 0797, 0967

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

S. Aulehlová *Aulehlová*
O. Kovářová *Kovářová*
2

**DATE OF
ACCEPTANCE:**
18.12.2024

**DATE OF
EXAMINATION:**
06.01. – 09.01.2025

**DATE OF
ISSUE:**
09.01.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to rubbing


was tested according to ČSN EN ISO 105-X12

- rubbing conditions: dry / wet (wetting of rubbing cloth: 100 %)
- rubbing finger: for textiles [diameter (16±0,1) mm; downward force (9±0,2) N]
- climatic conditions during testing: temperature (20±2) °C, RH (65±2) %
- time of air-conditioning of samples: 4 hours

Result: grade of grey scale (staining to cotton rubbing cloth according to ČSN EN ISO 105-A03)

Sample description	Results	
Re-wool 2, 0198	staining in warp / weft direction	
	dry conditions	4-5 / 5
	wet conditions	4 / 5
Re-wool 2, 0397	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	4-5 / 4-5
Re-wool 2, 0577	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	4-5 / 4-5
Re-wool 2, 0767	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	4-5 / 4-5
Re-wool 2, 0797	staining in warp / weft direction	
	dry conditions	4-5 / 5
	wet conditions	5 / 5
Re-wool 2, 0967	staining in warp / weft direction	
	dry conditions	4-5 / 5
	wet conditions	5 / 5

Approved by:


 Markéta Hrubanová
 Head of Testing Laboratories

End of report

