

#### Guest

Design: Louise Sigvardt

Type: Upholstery, panel fabric Composition: 100% recycled polyester

Yarn type: Chenille, filament

Binding: Jacquard

Width: Approx. 140 cm, 55 inches Weight: Approx. 480 g/lin.m, 15 oz/ly

Repeat: None

Colour difference may occur

Cleaning: Vacuum clean frequently, ideally every week if fixed covers. Remove stains as soon as they occur, with clean warm water or sparkling water. Extraction clean when necessary. No ironing, only steaming. Steaming might be necessary to remove pressure marks. Extraction cleaning might dissolve water-based glue. Pay attention to temperature and amount of cleaning fluid. Also washable at 30°C, half wash load. Drip drying. Mount in moist condition. Shrinkage app. 1% at 30°C.. Disinfection, see kvadrat.dk

More info: Care and maintenance kvadrat.dk

30/ X ⊠ Z P







# Guest

### **Abrasion**

App. 100.000 Martindale rubs, EN ISO 12947 Colour change: note 4-5 after 6000 rubs

#### Pilling

Note 4, EN ISO 12945

### Seam slippage

Seam parallel to warp: 2.5 mm parallel to weft: 3.0 m EN ISO 13 936-2 180 Newton

### Lightfastness

Note 5-7 ISO 105-B02

### Fastness to rubbing

Dry note 4-5 ISO 105-X12 Wet note 4-5 ISO 105-X12

# **Absorption**

150 mm airgap 0.70/Class C (flat), 0.85/Class B (waved) EN ISO 354 100 mm airgap 0.60/Class C (flat), 0.75/Class C (waved) EN ISO 354

### **Airflow**

757 Pa s/m EN 29053

## Flame resistance

AS/NZS 1530.3 AS/NZS 3837 class 2 ASTM E84 Class A Unadhered ASTM E84 Class A Adhered BS 5852 Part 1 with treatment \* BS 5852 Crib 5 with treatment \* BS 7176 Low Hazard EN 1021-1/2 IMO FTP Code 2010 : Part 8 NFPA 701 with treatment \* SN 198 898 5.2 with treatment \* US Cal. Bull. 117-2013

Free from added flame retardant chemicals as standard

\* To pass this test flame retardant treatment is necessary. We are looking into more environmentally friendly alternatives but for now the external finisher may use a treatment containing halogen based flame retardants



### **ACT Guidelines Woven fabrics**

### Flammability

US Cal. Bull. 117-2013

# **Dry & Wet Crocking AATCC 8**

Dry Crocking: Grade 4.5-5.0 Wet Crocking: Grade 4.0-5.0

### Colour Fastness to Light AATCC 16

Grade 4.0-5.0 minimum 40 hours

# **Physical properties**

Pilling Class 4 ASTM D4970 Breaking Strength warp 347 / weft 96 lbs. ASTM D5034 Seam Slippage warp 98 / weft 107 lbs. ASTM D 4034

### **Abrasion ASTM D4966**

100.000 cycles Martindale - High Traffic / Public Spaces

# **Quality benefits**

Complies with Möbelfakta Good abrasion Very good lightfastness Washable

### **Environmental benefits**

Complies with EU Ecolabel
Recycled content
Free of intentionally added PFAS
Mono-material designed for circularity
REACH compliant
Californian Proposition 65 list compliant
LBC Red list compliant
Healthier Hospitals compliant

## Green building certificates

Greenguard Gold: Low chemical emission Health Product Declaration (HPD): Declaring textile content and substance

# Country of origin

Turkey

### Launch

2024

### Warranty

10 years. See terms and conditions on kvadrat.dk

Kvadrat packaging and cardboard is recyclable. Cardboard material is FSC certified and / or contains recycled content.

Kvadrat A/S is ISO 9001 and ISO 14001 certified

For further information kvadrat.dk

