



For the Account of: Kvadrat A/S
Lundbergsvej 10
DK-8400 Ebeltøft

Client's Identification: HERO 2
Alta DWR Drapery

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

TEST RESULTS

| Specimen | Mass Initial (g) | Mass Final (g) | Mass Loss (%) | Drip Burn (s) | Afterflame (s) |
|----------|------------------|----------------|---------------|---------------|----------------|
| 1 | 27.1 | 21.4 | 21 | 0.0 | 0.0 |
| 2 | 26.6 | 23.3 | 12 | 0.0 | 0.0 |
| 3 | 26.3 | 22.0 | 16 | 0.0 | 0.0 |
| 4 | 25.9 | 22.1 | 15 | 0.0 | 0.0 |
| 5 | 26.2 | 21.7 | 17 | 0.0 | 0.0 |
| 6 | 27.2 | 20.3 | 25 | 0.0 | 0.0 |
| 7 | 26.8 | 20.8 | 22 | 0.0 | 0.0 |
| 8 | 26.4 | 20.6 | 22 | 0.0 | 0.0 |
| 9 | 26.1 | 22.5 | 14 | 0.0 | 0.0 |
| 10 | 26.6 | 22.0 | 17 | 0.0 | 0.0 |
| Average | 26.5 | 21.7 | 18 | 0.0 | 0.0 |

NOTES

Approximate weight (oz./sq. yd): 13.0

Standard Deviation: 4.2

Mean + 3 SD: 30.6

Product Configuration: ☒ Single Layer ☐ Multi Layer
Material Tested: Initially
Test Environment: 70 ±4°F, 50 ±5% Relative Humidity
Conditioning: ☒ Oven at 220°F (30 minutes) ☐ 70 ±4°F & 65 ±5%RH for 24 hours
Sampling: As Received
Intended End-use: Drapery

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply
☐ Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 03/26/2025