

For the Account of: Kvadrat A/S
Lundbergsvej 10
DK-8400 Ebeltøft

Client's Identification: HERO HEATHER
Alta DWR Drapery

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	26.2	22.4	15	0.0	0.0
2	25.7	21.5	16	0.0	0.0
3	26.0	20.4	22	0.0	0.0
4	25.9	22.4	14	0.0	0.0
5	26.9	23.6	12	0.0	0.0
6	25.2	19.5	23	0.0	0.0
7	25.2	21.0	17	0.0	0.0
8	25.9	22.8	12	0.0	0.0
9	25.8	20.0	22	0.0	0.0
10	26.9	24.4	9	0.0	0.0
Average	26.0	21.8	16	0.0	0.0

NOTES

Approximate weight (oz./sq. yd): 12.8

Standard Deviation: 4.8

Mean + 3 SD: 30.4

Product Configuration: ☒ Single Layer ☐ Multi Layer
Material Tested: Initially
Test Environment: 70 ±4°F, 50 ±5% Relative Humidity
Conditioning: ☒ Oven at 220°F (30 minutes) ☐ 70 ±4°F & 65 ±5%RH for 24 hours
Sampling: As Received
Intended End-use: Drapery

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply
☐ Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 03/26/2025