

For the Account of: Kvadrat A/S  
Lundbergsvej 10  
DK-8400 Ebeltøft

Client's Identification: FLOYD  
Alta DWR Drapery

## CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

### TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	16.5	12.6	24	4.0	0.0
2	16.6	11.3	32	3.0	0.0
3	16.4	11.5	30	1.0	0.0
4	16.5	12.1	27	0.0	0.0
5	16.6	11.9	28	0.0	0.0
6	16.6	11.0	34	3.0	0.0
7	16.4	12.5	24	2.0	0.0
8	16.6	11.5	31	2.0	0.0
9	16.5	11.4	31	0.0	0.0
10	16.5	11.7	29	4.0	0.0
Average	16.5	11.8	29	1.9	0.0

### NOTES

Approximate weight (oz./sq. yd): 8.1      Standard Deviation: 3.3      Mean + 3 SD: 38.9

Product Configuration: ☒ Single Layer    ☐ Multi Layer  
Material Tested: Initially  
Test Environment: 70 ±4°F, 50 ±5% Relative Humidity  
Conditioning: ☒ Oven at 220°F (30 minutes)    ☐ 70 ±4°F & 65 ±5%RH for 24 hours  
Sampling: As Received  
Intended End-use: Drapery

### ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies  
☐ Does Not Comply  
☐ Testing of 10 additional specimens is required

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 04/03/2025