

Test Report

Report Number:
225848-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1 DK-
2630 Taastrup +45
72 20 20 00

info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.:
225848 Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Sample of upholstery fabric designated: Asator 194. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 15 November 2023.

Period: The test took place from 16 November 2023 to 27 November 2023.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
194	Sample of upholstery fabric Designated: Asator 194 Composition: 100% cotton Approximate mass per area: 416 g/m ²	



Results

Test of Sample of upholstery fabric designated: Asator 194

Determination of the abrasion resistance of fabrics by the Martindale method

Part 2: Determination of specimen breakdown

EN ISO 12947-2:2016

Test conditions: 21°C, 65% RH

Colour change: DS EN 20105-A02:1997:1997 (1-5 scale, 5 best rating)

Sample			
194	(none)	Mass: 795 g Nominal pressure: 12 kPa End-point: Nap worn away	>100000 >100000 >100000 End result: >100000 Colour change: Note 4-5 after 6000 rubs

EN ISO 12945-2:2020

1-5 scale, 5 best rating

Test conditions: 21°C, 65% RH

Evaluation:

EN ISO 12945-4:2020

Sample			Results
194	(none)	Number of test specimens: 3 Number of observers: 2 Abradant: Wool abradant fabric Loading mass: 415 g	
			1 5 5 5 5 5 5
			2 5 5 5 5 5 5
			3 5 5 5 5 5 5
			1 4-5 4-5 4-5 4-5 4-5 4-5
			2 4-5 4-5 4-5 4-5 4-5 4-5
			3 4-5 4-5 4-5 4-5 4-5 4-5
			1 4-5 4-5 4-5 4-5 4-5 4-5
			2 4-5 4-5 4-5 4-5 4-5 4-5
			3 4-5 4-5 4-5 4-5 4-5 4-5