

Our Ref: SW/SW


3 February 2025

Report 429726 Rev. 1**Page: 1 of 7**

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Laura Wood

| | |
|--------------------------|--|
| DATE RECEIVED | : 23 DEC 2024 |
| QUALITY/REFERENCE | : TECHNICOLOUR - 30 SHADES |
| REPUTED FIBRE CONTENT | : 100% WOOL |
| FABRIC DESCRIPTION | : WOVEN |
| COLOUR/DESIGN | : 110, 120, 140, 150, 160, 190, 200, 210, 220, 230, 250, 260, 340, 360, 370, 520, 550, 620, 650, 690, 810, 820, 830, 860, 870, 890, 930, 940, 970, 990 |
| ORDER NUMBER | : 5415 |
| PERFORMANCE STANDARD | : GENERAL |
| TEST PERFORMANCE DATE(S) | : 23/12/2025 |



REQUEST: Colour fastness to Light

3 February 2025

Report 429726 Rev. 1**Page: 2 of 7****S. WISEMAN**
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of Eurofins MTS Consumer Product Testing Services Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

This report replaces report number 429726 dated 23/12/24. remove pass fail comments

3 February 2025

Report 429726 Rev. 1**Page: 3 of 7****COLOUR FASTNESS TO:****BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7**

Colour 110

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 120

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 140

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 150

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 160

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 190

| | |
|--|--------------|
| | Shade change |
| | 7 |

3 February 2025

Report 429726 Rev. 1**Page: 4 of 7****COLOUR FASTNESS TO:****BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7**

Colour 200

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 210

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 220

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 230

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 250

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 260

| | |
|--|--------------|
| | Shade change |
| | 7 |

3 February 2025

Report 429726 Rev. 1**Page: 5 of 7****COLOUR FASTNESS TO:****BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7**

Colour 340

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 360

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 370

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 520

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 550

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 620

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

3 February 2025

Report 429726 Rev. 1**Page: 6 of 7****COLOUR FASTNESS TO:****BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7**

Colour 650

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 690

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 810

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 820

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 830

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 860

| | |
|--|--------------|
| | Shade change |
| | 6-7 |

3 February 2025

Report 429726 Rev. 1**Page: 7 of 7****COLOUR FASTNESS TO:****BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7**

Colour 870

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 890

| | |
|--|--------------|
| | Shade change |
| | 7 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 930

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 940

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 970

| | |
|--|--------------|
| | Shade change |
| | 6 |

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 7

Colour 990

| | |
|--|--------------|
| | Shade change |
| | 7 |