



TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0466-01

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: Miori Outdoor
(according to the customer order) Use surface: 100 % polypropylene
Colours: 0171, 0181, 0211, 0261, 0381, 0541, 0741

Sample description on page 2

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

S. Aulehlová *Aulehlová*
O. Kovářová *Kovářová*
3

**DATE OF
ACCEPTANCE:**
04.04.2025

**DATE OF
EXAMINATION:**
06.04. – 24.04.2025

**DATE OF
ISSUE:**
24.04.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Description of samples:



Miori Outdoor
0171
volcanic soil



Miori Outdoor
0181
river pebbles



Miori Outdoor
0211
limestone



Miori Outdoor
0261
warm clay



Miori Outdoor
0381
black soil



Miori Outdoor
0541
red earth



Miori Outdoor
0741
blue clay





Determination of colour fastness to artificial light: Xenon arc fading lamp test


was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,3 MJ/m²

Result: grade of blue scale

Sample	Results
Miori Outdoor, colour 0171	colour change 8
Miori Outdoor, colour 0181	colour change 8
Miori Outdoor, colour 0211	colour change 8
Miori Outdoor, colour 0261	colour change 8
Miori Outdoor, colour 0381	colour change 8
Miori Outdoor, colour 0541	colour change 8
Miori Outdoor, colour 0741	colour change 8

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report



TITV e. V. • Zeulenrodaer Str. 42 • 07973 Greiz

Kvadrat Czech Republic s.r.o
Kročehlavská 1039
272 03 Kladno-Dubí
Czech Republic**Test report 47/1_B/25**
Replaces test report 47/1_A/25

Ha

23/04/2025

page 1 of 2

Customer: Ms. Martina Novotná
Assignment from: 05/02/2025
Received: 06/02/2025Assignment:

No.	Test	Standard Test conditions
1.	Colour fastness to artificial weathering: Xenon arc fading lamp test	DIN EN ISO 105-B04:1997 Used machine: Q-Sun (Xe-3-HDS) Used method: method 2 Subcontracted implementation and evaluation

Samples:

Coding for test	Identification by customer
Sample 1	<u>Miori Outdoor</u> Colours: 0171, 0181, 0211, 0261, 0381, 0541, 0741 Material composition: 100 % Polypropylene

Sampling: The samples were taken by the customer.Realisation
of the test:

The measurement samples were taken and tested in compliance with the above-mentioned regulations.

Testing period: 10/02/2025 - 17/04/2025

Test results:1. Fastness to artificial weathering**Sample 1**

Colour	Grade
0171	7
0181	7
0211	7
0261	7
0381	7
0541	7
0741	7

The colour change is evaluated according to the blue scale.
A grade of 8 is the best grade and a grade of 1 is the worst grade.

Correction: The treated samples were re-evaluated using a blue scale.

The testing results are exclusively related to the sample under conditions as received.

Without written permission of the testing laboratory it is inhibited to copy this report partially.

p.p. S. Klobes

Dr Klobes
Head of the Testing Centre