



**Febrik bv**  
**Terheijdenstraat 3C**  
**4811 AW BREDA**  
**Netherlands**

**Your notice of**  
 12-07-2024

**Your reference**

**Date**  
 22-07-2024

## Analysis Report 24.03831.01

Required tests :

**ISO 12947-2 (1998)/cor.1 (2002)      Determination of the abrasion resistance - Martindale**

Sample id	Information given by the client	Date of receipt
T2414507	MYLLA	12-07-2024



Elke Van De Walle  
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Samples

T2414507  
MYLLA





**Reference: T2414507 - MYLLA**

**Determination of the abrasion resistance - Martindale**

Date of ending the test 19-07-2024  
Standard used ISO 12947-2 (1998)/cor.1 (2002)  
Product standard EN 14465 (2003) + A1 (2006)

Deviation from the standard -  
Conditioning 20°C, relative humidity 65%  
Apparatus Martindale Wear and Abrasion Tester  
Pressure on test specimen 12 kPa  
Abradant Standard wool fabric  
Type of the felt Woven felt  
Approximate g/m<sup>2</sup> > 500  
Number of test specimens 4

Assessment of colour change according to the grey scales (ISO 105 A02)  
Assessment after 3 000 rubs 4  
Test end point Knitted - 1 loop completely damaged

Specimen	Number of rubs	Final result
#1	60 000	50 000
#2	60 000	50 000
#3	60 000	50 000
#4	60 000	50 000
Minimum value	60 000	50 000