

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .


Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

**Test Sponsor :** FEBRIK  
Terheijdenstraat 3C  
NL-4811 AW Breda  
Netherlands

**Test Number :** 24-002968  
**Issue Date :** 5/08/2024  
**Print Date :** 26/08/2024

**Sponsor Product :** Clients Ref : "Mylla"  
Knitted fabric  
Colour : Mustard  
End Use : Upholstery  
Nominal Composition : 100% Recycled Polyester  
Nominal Mass per Unit Area/Density : 625g/m2  
Nominal Thickness : 2mm



72197

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

**Test Sponsor :** FEBRIK  
Terheijdenstraat 3C  
NL-4811 AW Breda  
Netherlands

**Test Number :** 24-002968  
**Issue Date :** 5/08/2024  
**Print Date :** 26/08/2024

Product Group Number Classification : 2

Average Specific Extinction Area : 151.3 m<sup>2</sup>/kg



Chris Campbell  
Client Relations Manager

72197

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.