

# kvadrat

Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft Denmark  
T +45 89 53 18 66 F +45 89 53 18 00  
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

## Fastness to rubbing ISO 105-X12

### Technicolour

| Colour number | Dry condition | Wet Condition |
|---------------|---------------|---------------|
| 110           | 5             | 5             |
| 120           | 5             | 5             |
| 140           | 4-5           | 4-5           |
| 150           | 4-5           | 4-5           |
| 160           | 4-5           | 4-5           |
| 190           | 4-5           | 3-4           |
| 200           | 5             | 5             |
| 210           | 5             | 5             |
| 220           | 5             | 5             |
| 230*          | 4-5           | 4             |
| 250           | 4-5           | 4-5           |
| 260           | 4-5           | 4-5           |
| 340           | 4-5           | 4-5           |
| 360*          | 4-5           | 4             |
| 370           | 4-5           | 4-5           |
| 520           | 4-5           | 4-5           |
| 550           | 4-5           | 4-5           |
| 620           | 4-5           | 4-5           |
| 650           | 4-5           | 4             |
| 690*          | 4-5           | 3-4           |

www.kvadrat.dk

| Colour number | Dry condition | Wet Condition |
|---------------|---------------|---------------|
| 810           | 5             | 5             |
| 820           | 4-5           | 4-5           |
| 830*          | 4-5           | 3-4           |
| 860*          | 4-5           | 4             |
| 870*          | 4-5           | 3-4           |
| 890*          | 4-5           | 3-4           |
| 930*          | 4-5           | 4             |
| 940*          | 4-5           | 4             |
| 970*          | 4-5           | 3-4           |
| 990*          | 4-5           | 3-4           |

\*Test report TZU AZL 25/0523 29.04.2025  
Internal test LH/Ih 2024.05.02