



TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 24/0961-02

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltøft
Denmark

SAMPLE: Set In
(according to the customer order) Item number: 5545
Fibre composition: 100 % polyester (Recycled Trevira CS)
Colours: 0100, 0200, 0220, 0240, 0340, 0640, 0170, 0840, 0740,
0150, 0130, 0230

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

M. Hrubanová *M. Hrubanová*
S. Aulehlová *S. Aulehlová*
2

**DATE OF
ACCEPTANCE:**
20.08.2024

**DATE OF
EXAMINATION:**
27.08.-12.09.2024

**DATE OF
ISSUE:**
28.03.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to artificial light: Xenon arc fading lamp test


was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 18,8 MJ/m²

Result: grade of blue scale

Sample	Results
Set In, colour 0100	colour change 8
Set In, colour 0200	colour change 7
Set In, colour 0220	colour change 8
Set In, colour 0240	colour change 7-8
Set In, colour 0340	colour change 6-7
Set In, colour 0640	colour change 6
Set In, colour 0170	colour change 5-6
Set In, colour 0840	colour change 6-7
Set In, colour 0740	colour change 6
Set In, colour 0150	colour change 6
Set In, colour 0130	colour change 7
Set In, colour 0230	colour change 7

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report





TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 24/1219-03

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltøft
Denmark

SAMPLE: Set In
(according to the customer order) Item number: 5545
Fibre composition: 100 % polyester (Recycled Trevira CS)
Colours: 0120, 0360, 0960

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

M. Hrubanová
S. Aulehlová
2

**DATE OF
ACCEPTANCE:**
16.10.2024

**DATE OF
EXAMINATION:**
17.10.-30.10.2024

**DATE OF
ISSUE:**
28.03.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to artificial light: Xenon arc fading lamp test

was tested according to ČSN EN ISO 105-B02


- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 19,5 MJ/m²

Result: grade of blue scale

Sample	Results
Set In, colour 0120	colour change 6
Set In, colour 0360	colour change 5-6
Set In, colour 0960	colour change 5-6

Approved by:

End of report


Markéta Hrubanová
Head of Testing Laboratories

