

For the Account of: Kvadrat A/S
Lundbergsvej 10
DK-8400 Ebeltøft

Client's Identification: SET UP

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2019 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	13.3	9.0	32	0.0	0.0
2	13.6	8.8	35	0.0	0.0
3	13.8	8.9	36	0.0	0.0
4	13.5	9.6	29	0.0	0.0
5	13.4	8.3	38	0.0	0.0
6	13.6	8.9	35	0.0	0.0
7	13.4	8.8	34	0.0	0.0
8	13.6	10.1	26	0.0	0.0
9	13.6	9.9	27	0.0	0.0
10	13.8	9.4	32	0.0	0.0
Average	13.6	9.2	32	0.0	0.0

NOTES

Approximate weight (oz./sq. yd): 6.7

Standard Deviation: 4.0

Mean + 3 SD: 44.0

Product Configuration: ☒ Single Layer ☐ Multi Layer
Material Tested: Initially
Test Environment: 70 ±4°F, 50 ±5% Relative Humidity
Conditioning: ☒ Oven at 220°F (30 minutes) ☐ 70 ±4°F & 65 ±5%RH for 24 hours
Sampling: As Received
Intended End-use: Drapery

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply
☐ Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 03/26/2025