



For the Account of: Kvadrat A/S
 Lundbergsvej 10
 DK-8400 Ebeltøft

Client's Identification: MONO MIX

CERTIFICATE OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D434-95 as Modified by ASTM D3597-02(2013)

TEST RESULTS

Specimen	Warp Yarn Slippage (lbf)	Type of Failure	Specimen	Fill Yarn Slippage (lbf)	Type of Failure
1	19.1	SB	1	33.2	SB
2	23.9	SB	2	23.0	SB
3	26.8	SB	3	23.8	SB
4	26.1	SB	4	30.2	SB
5	21.2	SB	5	30.0	SB
Avg. Warp	23.5		Avg. Fill	28.0	

ABBREVIATIONS USED

- SB** Seam broke before 1/4" slippage - Results should reflect this
- SS** 1/4" slippage occurred - Note: Actual slippage of yarns is visible
- FB** Fabric broke before 1/4" slippage - Note: Actual breakage is visible


NOTES

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling:** As Received
- Equipment Used:** Tinius Olson H5KT Universal Testing Machine (CRE)
- Seam Description:** Per ASTM D3597-02
 - Seam Type** Standard Lockstitch
 - Stitches per Inch** 7 -8 stitches per inch
 - Needle Used** Chrome plated 0.063 inch diameter
 - Thread** No. 24-4 hard finish Z-twist cotton thread
- Material Tested:** As Received (no refurbishment), unless otherwise noted in Client Identification above

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Drapery fabrics over 6oz/sq. yard	25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 03/12/2025