



TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 24/1276-01

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: Fabric Sideway
(according to the customer order) Item number: 5549
Fibre composition: 100 % linen
Colours: 0101, 0111, 0221, 0641, 0791, 0951

**CONDITIONS OF
APPLICATION OF THE TEST
REPORT:**

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY: M. Hrubanová
CHECKED BY: O. Kovářová
NUMBER OF PAGES: 2

**DATE OF
ACCEPTANCE:**
01.11.2024

**DATE OF
EXAMINATION:**
01.11.-19.11.2024

**DATE OF
ISSUE:**
09.06.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to artificial light: Xenon arc fading lamp test


was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 19,7 MJ/m²

Result: grade of blue scale

Sample	Results
Sideway, colour 0101 – front side	colour change 5-6
Sideway, colour 0101 – back side	colour change 5-6
Sideway, colour 0111 – front side	colour change 6
Sideway, colour 0111 – back side	colour change 6
Sideway, colour 0221 – front side	colour change 6-7
Sideway, colour 0221 – back side	colour change 6
Sideway, colour 0641 – front side	colour change 4
Sideway, colour 0641 – back side	colour change 5
Sideway, colour 0791 – front side	colour change 6
Sideway, colour 0791 – back side	colour change 6
Sideway, colour 0951 – front side	colour change 4-5
Sideway, colour 0951 – back side	colour change 4-5

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report





TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic


TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0458-01

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: fabric Sideway
(according to the customer order) Item: 5549
Fibre composition: 100% linen
Colour: 0211



The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

**CONDITIONS OF
APPLICATION OF THE TEST
REPORT:**

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

O. Kovářová *Kovářová*
S. Aulehlová *Aulehlová*
2

**DATE OF
ACCEPTANCE:**
03.04.2025

**DATE OF
EXAMINATION:**
04.-23.04.2025

**DATE OF
ISSUE:**
24.04.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to artificial light: Xenon arc fading lamp test


was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,3 MJ/m²

Result: grade of blue scale

Sample	Results
Sideway col. 0211, front side	colour change 7
Sideway col. 0211, back side	colour change 6

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report

