

TFI-Report 25-000225-01

Functional and Quality Testing

Customer Kvadrat AS
Lundbergsvej 10
8400 Ebeltøft
DK

Product Textiler Bodenbelag/Textile floor covering
Miori Outdoor, col. 0171

This report includes 5 pages.



Aachen, 19.03.2025

Dr. Jacqueline Lemm



The present document is provided with an advanced electronic signature.

This report only applies to the tested samples and has been established to the best of our knowledge. Only the entire report shall be reproduced. Under no circumstances, extracts shall be used. Furthermore, we apply the "General Terms and Conditions for the Execution of Contracts" of the TFI Aachen GmbH, also with regard to the order execution.

The test result does not include any addition or deduction for uncertainties due to measurement, sample preparation, sample collection and production tolerances.

1 Transaction

Order date 06.02.2025
Your reference Martina Novotna
Product designation Miori Outdoor, col. 0171

TFI sample number 2500227

Date of sample receipt 10.02.2025
Sampling performed by Auftraggeber/Customer

Testing period 11.03.2025 - 18.03.2025

Test order:

Change in appearance according ISO 10361 - Hexapod ^a

a ... Die mit a gekennzeichneten Ergebnisse basieren auf nach EN ISO/IEC 17025 akkreditierten Prüfungen./The reports marked a are based on tests accredited in accordance with EN ISO/IEC 17025.

Responsible at TFI:



Manuela Schönbein
+49 241 9679230
m.schoenbein@tfi-aachen.de

2 Product description

TFI sample number 2500227



Total thickness in mm	* Ca. 10
Total mass per unit area in g/m ²	* 2700
Type of delivery	In Probengröße angeliefert/Supplied in sample size

Sample setup

*Angabe des Auftraggebers/Customer Information

3 Results

Change in appearance median - Shortterm Hexapod	4
Change in appearance median - Longterm Hexapod	2.5

The measurement results are evaluated without consideration of the measurement uncertainty with reference to compliance with limit values, unless otherwise specified by the test standard.

4 Partial Reports

Change in appearance according ISO 10361 - Hexapod

Partial Report AV - Changes In Appearance

1 Transaction

TFI sample number 2500227

2 Test Method / Requirements

ISO 10361:2015	Production of changes in appearance by means of Vettermann drum and hexapod tumbler tester
Assessment standard	EN ISO 9405:2017
Deviation	No individual results of assessors given
Test method	method B (Hexapod)
Type of underlay	none
Number of assessors	3
Type of vacuum cleaner	Vorwerk Kobold VT270 / EB370
Assessment scale	ISO loop

3 Results

Parameter	Short-term wear (4,000 cycles)		Long-term wear (12,000 cycles)	
	Mean value	Median value	Mean value	Median value
Assessment	4.0	4.0	2.5	2.5
Grey Scale	4.5	4-5	3.7	3-4
Dominant property	structure		structure, colour	
Classification according EN 1307, table 15	class 31			
Classification according EN 14215, table 3	class 21			

Comments / special observations: none