

SAHCO

1831



Zade

Type: Upholstery

Composition: 58% viscose, 21% cotton, 21% polyester

Yarn type: Spun

Binding: Epinglé

Width: Approx. 140 cm, 55 inches

Weight: Approx. 1060 g/lin.m, 34 oz/ly

Repeat: Approx. 6 cm, 2.4 inches V, 8.5 cm, 3.3 inches H

Colour difference may occur

Cleaning: Vacuum clean frequently, ideally every week.

Remove stains as soon as they occur, with clean warm water or sparkling water. Extraction clean when necessary.

Important that cleaning is done along the loops. Extraction cleaning might dissolve water based glue. Pay attention to temperature and amount of cleaning fluid.

Disinfection, see kvadrat.dk/en/sahco



10^{year}
warranty



Abrasion

Approx. 35.000 Martindale rubs, EN ISO 12947

Pilling

Note 5, EN ISO 12945

Seam slippage

Seam parallel to warp: 2.0 mm parallel to weft: 1.5 mm

EN ISO 13 936-2 180 Newton

Snagging

Note 2 ICI Testmethod FAB 29, Tumble-Box

Lightfastness

Note 6-7 ISO 105-Bo2

Fastness to rubbing

Dry note 4-5 ISO 105-X12

Wet note 4-5 ISO 105-X12

Flame resistance

AS/NSZ 3837 class 2

BS 5852 Part 1

BS 7176 Low Hazard

EN 1021-1/2

IMO FTP Code 2010:Part 8

US Cal. Bull. 117-2013

Free from added flame-retardant chemicals as standard

SAHCO

1831

Characteristics

An epinglé construction create depth to the textile and due to the height of the pile small gaps between the loops can and will occur in use.

Small irregularities may occur during production – might be more noticeably in contrast colours

Due to the high contrast between yarn colours a stripe effect may occur. This is not seen as a fault but as a characteristic for this design

During handling, use and cleaning the loops may be flattened due to heat, humidity and pressure. This effect, is however typical for epinglé textiles.

Pressure marks should be possible to remove by light steaming and brushing carefully along the loops with a soft brush.

ACT Guidelines Woven fabrics

Flammability

US Cal. Bull. 117-2013

Dry & Wet Crocking AATCC 8

Dry Crocking: Grade 4.5-5.0

Wet Crocking: Grade 4.0-5.0

Colour Fastness to Light AATCC 16

Grade 5.0 minimum 40 hours

Physical properties

Pilling Class 5 ASTM D4970

Breaking Strength warp 215 / weft 411 lbs, ASTM D5034

Seam Slippage warp 113 / weft 127 lbs, ASTM D4034

Abrasion ASTM D4066

35.000 cycles Martindale –Low Traffic / Private Spaces

Quality benefits

Good abrasion

Very good lightfastness

Flame retardant

Environmental benefits

REACH compliant

Californian Proposition 65 list compliant

LBC Red list compliant

Healthier Hospitals compliant

Free of intentionally added FPAS

Green building certificates

Greenguard Gold: Low chemical emission

Health Product Declaration (HPD): Declaring textile content and substance

Country of origin

India

Launch

2025

Warranty

10 years. See terms and conditions on kvadrat.dk

Kvadrat packaging and cardboard is recyclable. Cardboard material is FSC certified and / or contains recycled content.

For further information

kvadrat.dk/en/sahco