



TESTING LABORATORY  
Cejl 480/12, 602 00 Brno, Czech Republic

**TESTING LABORATORY 1001**  
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

# TEST REPORT

AZL 25/0036

**CUSTOMER:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft  
Denmark

**SAMPLE:** Fabric Casera  
(according to the customer order) Fibre composition: 90% recycled polyester FR, 10% polyester FR  
Colour: 0123, 0133, 0393, 0633, 0653, 0793, 0923, 0953, 0203, 0223, 0233, 0263, 0343, 0373, 0363, 0253, 0723, 0323, 0753, 0773

**CONDITIONS OF  
APPLICATION OF THE TEST  
REPORT:**

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

**PREPARED BY:** O. Kovářová *Kovářová*  
**CHECKED BY:** S. Aulehlová *Aulehlová*  
**NUMBER OF PAGES:** 3

**DATE OF  
ACCEPTANCE:**  
19.12.2024

**DATE OF  
EXAMINATION:**  
07.-24.01.2025

**DATE OF  
ISSUE:**  
07.07.2025



+420 543 426 730  
www.tzu.cz  
azl@tzu.cz



***Determination of colour fastness to artificial light: Xenon arc fading lamp test***

was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,4 MJ/m<sup>2</sup>

**Result:** grade of blue scale


Sample	Results
0123	colour change 7-8
0133	colour change 7-8
0393	colour change 7
0633	colour change 7
0653	colour change 7
0793	colour change 7
0923	colour change 7
0953	colour change 7
0203	colour change 7
0223	colour change 7-8
0233	colour change 7-8
0263	colour change 7-8
0343	colour change 7-8
0373	colour change 7-8
0363	colour change 7-8
0253	colour change 7-8
0723	colour change 7-8
0323	colour change 7-8





Sample	Results
0753	colour change 7-8
0773	colour change 7-8

Approved by:

  
Markéta Hrubanová  
Head of Testing Laboratories

End of report

