



# Confidential Report

**Our Ref: 23/63004B/03/25**





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 09 April 2025

Our Ref: 23/63004B/03/25  
Your Ref: ---

Page: 1 of 4

**Client:** **Kvadrat A/S**

Lundbergsvej 10  
8400 Ebeltoft  
Denmark

**Job Title:** Fire Test on One Fabric Sample

**Clients Order Ref:** --

**Date of Receipt:** 24 March 2025

**Date Test Started:** 09 April 2025

**Description of Sample:** One sample of fabric, which was referenced by the client as;  
Daybreak 3, item 1073, 100% REC PES FR

**Work Requested:** We were asked to make the following fire test:  
BS 5867: Part 2:Type B:2008 (2015)

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited



1066

Note: This report relates only to the items tested.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 09 April 2025

Our Ref: 23/63004B/03/25  
Your Ref: ---

Page: 2 of 4

Client: **Kvadrat A/S**

## **BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds**

### **Pre-treatment**

The sample was not subjected to any water soaking procedure.

### **Conditioning**

The test specimens were conditioned for at least 24 hours in the standard atmosphere of  $65 \pm 5$  % relative humidity (R.H.) and  $20 \pm 2$  °C.

### **Testing**

Three specimens from both length and width were tested in accordance with BS EN ISO 15025: Procedure A (surface ignition):2002.

Each specimen was subjected to an applied flame using propane and a 15 second flame application time. The results obtained (shown in the table below) were assessed according to the requirements of BS 5867: Part 2:Type B:2008 (2015).



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
 Telephone: +44 (0) 113 259 1999  
 Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
 Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 09 April 2025

Our Ref: 23/63004B/03/25  
 Your Ref: ---

Page: 3 of 4

Client: **Kvadrat A/S**

### Results - Testing as received.

Specimen No.	Length			Width		
	1	2	3	4	5	6
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Occurrence of debris	No	No	No	No	No	No
Ignition of filter paper from debris	No	No	No	No	No	No
Hole formation	Yes	Yes	Yes	Yes	Yes	Yes
Afterflame (s)	0	0	0	0	0	0
Afterglow (s)	0	0	0	0	0	0

Requirements - Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, if the second 6 specimens all pass the result is a pass.

When testing multilayer specimens, a hole formation should be reported in each separable layer.

**Result: Pass**

### Note

The material received no pre-treatment as the fabric stated to be inherently flame retardant. (Inherently FR)

### Comment

The fabric meets the Type B performance requirements of BS 5867: Part 2: 2008

The material should be identified with the manufacturers name, trademark or other identifying mark, the statement 'Flammability complies with the requirements of BS 5867: Part 2, Type B and instructions of any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS EN 23758 and taking account of the pre-treatment used in this test and the requirements of Clause 4 of BS 5867: Part 2: 2008 (2011). If the fabric is unsuitable for cleansing, this shall be stated.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 09 April 2025

Our Ref: 23/63004B/03/25  
Your Ref: ---

Page: 4 of 4

**Client:** Kvadrat A/S

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.


See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

## Uncertainty Budget

For the remaining criteria, measurements are not taken and the pass/fail is related to flame extremities and flaming debris, as such any risk of false acceptance/false rejection is inherent with this standard and would be outside of 95% probability in any case. As such UoM is Zero providing all input parameters are correct.

Timings:  $\pm 2$  seconds

Reported by:  R Walls, Laboratory Technician

Countersigned by:  B Bland, Technical Customer Service Officer

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.