

Independent Textile Testing Service, Inc.

Test No: 206294

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: Kvadrat Inc.

December 17, 2020

Subject: Sample(s) of carpet submitted for testing by the Customer and identified below:

Sample Identification: Kanon col. 0002
Kvadrat Rugs by Kinnasand

Test Method Conducted
ASTM D-5252 Hexapod Drum Tester
ISO/TR 10361 Hexapod Tumbler
Ratings Based on CRI TM-101 Photographic Scales
ASTM D-7330 Assessment of Surface Appearance Change in Pile Floor Coverings

APPARATUS: WIRA INSTRUMENTATION HEXAPOD TUMBLER CARPET TESTER

PROCEDURE:

The test specimen described above was subjected to the reported cycles of "Hexapod" tumbling, removing the specimen every 2,000 cycles for restoration by vacuuming.

A 6.7 Amp Shark handheld vacuum w/rotary brush was used, making four (4) forward and backward passes along the length of the specimen.

The samples were assessed using day-light equivalent vertical lighting (1500 lux). Samples were viewed at an angle of 45 degrees from 1½ meter distance, judging from all directions.

TEST RESULTS:

NUMBER OF HEXAPOD CYCLES	OVERALL APPEARANCE CHANGE
12,000	3.0

Key to Ratings
5 = Negligible or no change
4 = Slight change
3 = Moderate change
2 = Considerable change
1 = Severe change

President L. Kent Suddeth