



TESTING LABORATORY  
Cejl 480/12, 602 00 Brno, Czech Republic

**TESTING LABORATORY 1001**  
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

# TEST REPORT

AZL 25/0806-01

**CUSTOMER:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft  
Denmark

**SAMPLE:** Fabric Valenna  
(according to the customer order) Fibre composition: 100 % recycled polyester, Trevira cs  
Colours: 100, 120, 130, 170, 210, 230, 260, 680, 720, 790

**CONDITIONS OF  
APPLICATION OF THE TEST  
REPORT:**

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

**PREPARED BY:**  
**CHECKED BY:**  
**NUMBER OF PAGES:**

O. Kovářová *Kovářová*  
S. Aulehlová *Aulehlová*  
2

**DATE OF  
ACCEPTANCE:**  
20.08.2025

**DATE OF  
EXAMINATION:**  
06.05.-15.05.2025  
20.06.-14.07.2025

**DATE OF  
ISSUE:**  
21.08.2025



+420 543 426 730  
www.tzu.cz  
azl@tzu.cz



***Determination of colour fastness to artificial light: Xenon arc fading lamp test***

was tested according to ČSN EN ISO 105-B02


- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,3 (and 20,2) MJ/m<sup>2</sup>

Result: grade of blue scale

Sample	Results
Valenna, col. 100	colour change 7
Valenna, col. 120	colour change 6-7
Valenna, col. 130	colour change 5-6
Valenna, col. 170	colour change 5
Valenna, col. 210	colour change 6-7
Valenna, col. 230*	colour change 6-7
Valenna, col. 260*	colour change 7
Valenna, col. 680	colour change 5-6
Valenna, col. 720	colour change 7
Valenna, col. 790	colour change 7

\* Test results were taken from the Test report AZL 25/0590 issued on 16.05.2025 delivered by customer.

Approved by:

  
Markéta Hrubanová  
Head of Testing Laboratories

End of report

