



TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0174

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: Item number: **KUMO**
(according to the customer order) Fibre composition: 60,7% wool / 28,5% viscose / 8,0% linen / 2,8% nylon
Colours: 100, 110, 130, 170, 180, 210, 230, 240, 260, 380, 410, 660, 790, 680, 930, 950

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

O. Kovářová
S. Aulehlová
2

Kovářová
Aulehlová

DATE OF ACCEPTANCE:
29.1.2024

DATE OF EXAMINATION:
31.01.-12.02.2025

DATE OF ISSUE:
17.02.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz




Determination of colour fastness to artificial light: Xenon arc fading lamp test
was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,0 MJ/m²

Result: grade of blue scale

Sample	Results
KUMO, colour 100	colour change 7
KUMO, colour 110	colour change 7-8
KUMO, colour 130	colour change 7
KUMO, colour 170	colour change 6-7
KUMO, colour 180	colour change 7
KUMO, colour 210	colour change 7-8
KUMO, colour 230	colour change 7-8
KUMO, colour 240	colour change 8
KUMO, colour 260	colour change 8
KUMO, colour 380	colour change 8
KUMO, colour 410	colour change 5-6
KUMO, colour 660	colour change 7-8
KUMO, colour 790	colour change 7-8
KUMO, colour 680	colour change 7-8
KUMO, colour 930	colour change 5-6
KUMO, colour 950	colour change 8

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report





TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic


TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0699

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: Fabric Kumo
(according to the customer order) Fibre composition: 61 % wool / 28 % viscose / 8 % linen / 3 % nylon
Colours: 930



The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

**CONDITIONS OF
APPLICATION OF THE TEST
REPORT:**

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

O. Kovářová
S. Aulehlová
2

**DATE OF
ACCEPTANCE:**
27.05.2025

**DATE OF
EXAMINATION:**
29.05.-12.06.2025

**DATE OF
ISSUE:**
13.06.2025



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to artificial light: Xenon arc fading lamp test


was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,2 MJ/m²

Result: grade of blue scale

Sample	Results
Kumo, col. 930	colour change 4-5

Approved by:


Markéta Hrubanová

Head of Testing Laboratories

End of report

