



TESTING LABORATORY  
Cejl 480/12, 602 00 Brno, Czech Republic

**TESTING LABORATORY 1001**  
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

# TEST REPORT

AZL 25/1081

**CUSTOMER:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft  
Denmark

**SAMPLE:** Fabric Retta Blockout  
(according to the customer order) **Item number: KHPT 130**  
Fibre composition: polyester fabric with coloured blackout coating  
Colours: 112, 142, 162, 192, 222

## CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

**PREPARED BY:**  
**CHECKED BY:**  
**NUMBER OF PAGES:**

O. Kovářová

V. Zetelmannová

2

**DATE OF  
ACCEPTANCE:**  
26.08.2025

**DATE OF  
EXAMINATION:**  
27.08.-22.09.2025

**DATE OF  
ISSUE:**  
22.09.2025



+420 543 426 730  
www.tzu.cz  
azl@tzu.cz



***Determination of colour fastness to artificial light: Xenon arc fading lamp test***


was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample's rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,3 MJ/m<sup>2</sup>

Result: grade of blue scale

| Sample              | Results              |
|---------------------|----------------------|
| Retta Blockout, 112 | colour change<br>7-8 |
| Retta Blockout, 142 | colour change<br>8   |
| Retta Blockout, 162 | colour change<br>8   |
| Retta Blockout, 192 | colour change<br>8   |
| Retta Blockout, 222 | colour change<br>8   |

Approved by:

  
Markéta Hrubanová  
Head of Testing Laboratories

End of report

