

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

Group Number Assessment

(In accordance with AS 5637.1-2015)


This is to confirm that the product as described below has been tested by AWTA Product Testing.

Testing was performed in accordance with Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

Test Sponsor :	Kvadrat A/S Lundbergsvej 10 Ebeltoft 8400 Denmark Denmark	Test Number :	25-002020
		Issue Date :	30/05/2025
		Print Date :	20/08/2025

Sponsor Product :	Clients Ref : "Kumo" Woven fabric Colour : Grey End Use : Wall Covering Nominal Composition : 61% New Wool, worsted 28% Viscose, 8% Linen, 3% Nylon Nominal Mass per Unit Area/Density : Approx. 630g/m2 Nominal Thickness : Approx. 1.5mm
--------------------------	--



77337

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. Its transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, its disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

Test Sponsor :	Kvadrat A/S Lundbergsvej 10 Ebeltoft 8400 Denmark Denmark	Test Number :	25-002020
		Issue Date :	30/05/2025
		Print Date :	20/08/2025

Product Group Number Classification :	3	
Average Specific Extinction Area :	22.0	m ² /kg



Fiona McDonald
Testing Technologist

77337

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.