



Confidential Report

Our Ref: 29/03748A/01/26



Date: 9 February 2026

Our Ref: 29/03748A/01/26
Your Ref:

Page: 1 of 4

Client: **Kvadrat A/S**

Lundbergsvej 10
8400 Ebeltoft
Denmark

Job Title: Seam Slippage Test on One Sample of Fabric

Clients Order Ref: --

Date of Receipt: 26 January 2026

Description of Sample: One sample of fabric, referenced; Forestview 751, stated to be: 96% wool, worsted, 4% nylon.

Work Requested: We were asked to make the following test(s):

Seam Slippage - BS EN ISO 13936-2

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

This report relates only to the items tested.

All tests were carried out in the laboratories in Leeds, unless otherwise indicated.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.



Date: 9 February 2026

Our Ref: 29/03748A/01/26

Your Ref:

Page: 2 of 4

Client: **Kvadrat A/S**

Determination of the Slippage Resistance of Yarns at a Seam in Woven Fabric – BS EN ISO 13936-2: 2004 (2017) – 180N maximum force applied to specimens

Date of test: 04/02/26

Conditioning

Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles (BS EN ISO 139:2005 + A1:2011) of 65±4% r.h. and 20±2°C.

Results

180N maximum force applied to specimens, fabric breakdown (FB) or seam breakdown (SB) is recorded as a failure.

Direction	Spec No.	Seam Opening (mm)	Fabric / Seam Breakdown (N)	Direction	Spec No.	Seam Opening (mm)	Fabric / Seam Breakdown (N)
Warp way seam (Warp slippage)	1	4.0	No	Weft way seam (Weft slippage)	1	5.0	No
	2	4.0	No		2	4.0	No
	3	4.0	No		3	4.0	No
	4	5.0	No		4	5.0	No
	5	4.0	No		5	4.0	No
	Mean	4.0			Mean	4.0	



Date: 9 February 2026


Our Ref: 29/03748A/01/26
Your Ref:


Page: 3 of 4

Client: **Kvadrat A/S**

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Reported by:.......... K Marshall, Section Leader

Countersigned by:.......... J Brewster, Section Leader

Enquiries concerning this report should be addressed to Customer Services.



Date: 9 February 2026

Our Ref: 29/03748A/01/26

Your Ref:

Page: 4 of 4

Client: **Kvadrat A/S**

Uncertainty Budget

The overall uncertainty budget for BS EN ISO 13936-2 is as follows: -

Overall uncertainty $\pm 4.7\%$



1066