



AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D
Pineville, NC 28134
O: 704.405.2550
F: 704.543.9772
www.americanflamecoat.com

Client: Kvadrat Inc.
549 Ottawa Avenue NW
Grand Rapids, MI 49503

Mill: Kvadrat Inc. – TROPIC - 0270 - treated with FLAMECOAT
Report Number: 127239
Date: February 13, 2026

TEST RESULTS

NATIONAL FIRE PROTECTION ASSOCIATION STD.701-2019 – TEST 1 Small Scale

| Specimen | Residues (seconds) | Weight loss (%) |
|----------|--------------------|-----------------|
| 1 | 0.0 | 18.28 |
| 2 | 0.0 | 14.39 |
| 3 | 0.0 | 21.06 |
| 4 | 0.0 | 17.61 |
| 5 | 0.0 | 9.18 |
| 6 | 0.0 | 10.84 |
| 7 | 0.0 | 11.16 |
| 8 | 0.0 | 17.54 |
| 9 | 0.0 | 17.31 |
| 10 | 0.0 | 17.51 |
| Average | 0.0 | 15.49 |

Results: The Above Tested Material **Meets the Requirement**

Requirements:

Average percent weight loss cannot exceed 40% and any individual Specimen cannot exceed mean value plus three standard deviations.

Residue Flame:

Shall not continue to flame after reaching the floor of the tester for more than an average of two seconds per specimen for the sample of 10 specimens.

Sincerely,

Brad Souffrant

