

Our Ref: SW/LS/RM

11 July 2017

Report 299962

Page 1 of 2

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

DATE RECEIVED	: 23 JUN 2017
QUALITY/REFERENCE	: TONICA 39 SHADES
REPUTED FIBRE CONTENT	: 100% PES
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: VARIOUS
ORDER NUMBER	: 170616
PERFORMANCE STANDARD	: GENERAL

REQUEST: Colour fastness to light



S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

Report 299962

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
111 Smoke	6+
132 Sage	6+
171 Lt Green	6+
182 Mid Green	6+
192 Charcoal	6+
411 Yellow	6+
511 Orange	6+
611 Red	6+
612 Red	6+
672 Iris	6+
732 Blue	6+
831 Turquoise	6+
832 Turquoise	6+
962 Green	6+
531 Burnt Orange	6+
123 Mint	6+
223 Cream	6+
233 Stone	6+
353 Bark	6+
383 Bark	6+

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
523 Clay	6+
533 Clay	6+
543 New Orange	6+
613 Magnolia	6+
623 Granite	6+
633 Granite	6+
643 New Red	6+
693 Peat	6+
713 Sky	6+
723 Sky	6+
733 Aqua	6+
743 Aqua	6+
763 Petrol	6+
773 Marine	6+
813 Mint	6+
873 Teal	6+
923 Apple	6+
933 Leaf	6+
443 New Yellow	6+