

For the Account of

Kvadrat Inc
549 Ottave Ave
Grand Rapids, MI 49503

Client's Identification

OUTER VIEW

CERTIFICATE OF TESTING

TEST PERFORMED California Fire Marshal Title 19: Section 1237 Small Scale Test – Interior Materials Qualifications (Proposed Revision – 8/9/93)

TEST RESULTS

Specimen	Afterflame (s)	Char Length (in)
1	0.0	4.5
2	0.0	4.0
3	0.0	4.9
4	0.0	3.6
5	0.0	3.9
Avg. Warp	0.0	4.2
Specimen	Afterflame (s)	Char Length (in)
1	0.0	3.9
2	0.0	4.3
3	0.0	4.1
4	0.0	5.1
5	0.0	5.0
Avg. Fill	0.0	4.5

NOTES

Sampling As Recived
Fabric Weight (oz / sq.yd.) 6.2
Material Tested Initially

ACCEPTANCE CRITERIA

1. Average Flame Time (after flame) after removal of the flame source may not exceed **4.0 seconds** for length or width
2. Char length may not exceed **6.0 inches** for any individual specimen.
3. When a part of the char length is melt away due to heat from the flame source and not from propagating flame, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for fabrics weighing less than 4 oz./sq.yd. These specimens shall be marked with an asterisk (*) next to the char length.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 08/06/2026