TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/1099-01

CUSTOMER: **Kvadrat A/S**
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE:
(according to the customer order) **fabric Technicolour Sky**
Colours: 111, 211, 271, 331, 361, 391, 411, 611, 761, 791, 971, 931

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY: M. Hrubanová
CHECKED BY: O. Kovářová
NUMBER OF PAGES: 2

DATE OF ACCEPTANCE:	DATE OF EXAMINATION:	DATE OF ISSUE:
28.08.2025	29.08.-11.09.2025	26.09.2025

ilac-MRA
L 1001

AKREDITOVANÁ ZKUŠEBNÍ LABORATOŘ
TZÚ TEXTILNÍ ZKUŠEBNÍ ÚSTAV BRNO
1001

☎ +420 543 426 730
www.tzu.cz
azl@tzu.cz

Determination of colour fastness to artificial light: Xenon arc fading lamp test
was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample´s rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,4 MJ/m^2

Result: grade of blue scale

Sample	Results
Technicolour Sky, colour 111	colour change 8
Technicolour Sky, colour 211	colour change 8
Technicolour Sky, colour 271	colour change 7-8
Technicolour Sky, colour 331	colour change 7
Technicolour Sky, colour 361	colour change 8
Technicolour Sky, colour 391	colour change 7
Technicolour Sky, colour 411	colour change 8
Technicolour Sky, colour 611	colour change 8
Technicolour Sky, colour 761	colour change 7-8
Technicolour Sky, colour 791	colour change 7-8
Technicolour Sky, colour 971	colour change 7
Technicolour Sky, colour 931	colour change 8

Approved by:

Markéta Hrubanová
Head of Testing Laboratories

End of report

AKREDITOVANÁ ZKUŠEBNÍ LABORATOŘ
TZÚ
TEXTILNÍ ZKUŠEBNÍ ÚSTAV BRNO
1001