TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0108-01

CUSTOMER: **Kvadrat A/S**
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE:
(according to the customer order) **Technicolour Cloud**
Fibre composition: 100% recycled polyester FR
Colours: 950, 980, 130, 110, 740, 380, 210, 230, 780, 220

CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY: M. Hrubanová
CHECKED BY: O. Kovářová
NUMBER OF PAGES: 2

DATE OF ACCEPTANCE:	**DATE OF EXAMINATION:**	**DATE OF ISSUE:**
16.01.2025	17.01.-03.02.2025	26.09.2025

ilac-MRA
L 1001

AKREDITOVANÁ ZKUŠEBNÍ LABORATOŘ
TZÚ
TEXTILNÍ ZKUŠEBNÍ ÚSTAV BRNO
1001

☎ +420 543 426 730
www.tzu.cz
azl@tzu.cz

Determination of colour fastness to artificial light: Xenon arc fading lamp test
was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample´s rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 19,9 MJ/m^2

Result: grade of blue scale

Sample	Results
Technicolour Cloud, colour 950	colour change 8
Technicolour Cloud, colour 980	colour change 7
Technicolour Cloud, colour 130	colour change 8
Technicolour Cloud, colour 110	colour change 7-8
Technicolour Cloud, colour 740	colour change 8
Technicolour Cloud, colour 380	colour change 7
Technicolour Cloud, colour 210	colour change 7-8
Technicolour Cloud, colour 230	colour change 7-8
Technicolour Cloud, colour 780	colour change 7
Technicolour Cloud, colour 220	colour change 7-8

Approved by:

Markéta Hrubanová
Head of Testing Laboratories

End of report

AKREDITOVANÁ ZKUŠEBNÍ LABORATOŘ
TZÚ
TEXTILNÍ ZKUŠEBNÍ ÚSTAV BRNO
1001

TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic


TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 25/0785

CUSTOMER:
Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE:
(according to the customer order)
Fabric Spinning Jenny Dense
Fibre composition: 100 % recycled polyester FR
Colours: 250, 350



CONDITIONS OF APPLICATION OF THE TEST REPORT:

The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY: O. Kovářová Kovářová
CHECKED BY: S. Aulehlová Aulehlová
NUMBER OF PAGES: 2

DATE OF ACCEPTANCE:	**DATE OF EXAMINATION:**	**DATE OF ISSUE:**
13.06.2025	13.06.-23.06.2025	23.06.2025

ilac-MRA
L 1001

AKREDITOVANÁ ZKUŠEBNÍ LABORATOŘ TZÚ TEXTILNÍ ZKUŠEBNÍ ÚSTAV BRNO

☎ +420 543 426 730
www.tzu.cz
azl@tzu.cz

Determination of colour fastness to artificial light: Xenon arc fading lamp test
was tested according to ČSN EN ISO 105-B02

- instrument: QSUN-Xe2, model B02, air cooled Xe lamp
- lighting procedure: method 2
- sample´s rotation: not used
- exposure conditions: A1 - normal, adequate to mild zone (RH 40 %, BST (45±3) °C)
- approximate radiation energy: (300-400 nm): 20,6 MJ/m^2

Result: grade of blue scale

Sample	Results
Spinning Jenny Dense, col. 250	colour change 7
Spinning Jenny Dense, col. 350	colour change 8

Approved by:

Markéta Hrubanová
Head of Testing Laboratories

End of report

AKREDITOVANÁ ZKUŠEBNÍ LABORATOŘ
TZÚ
TEXTILNÍ ZKUŠEBNÍ ÚSTAV BRNO
1001