



TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 26/1056

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: Fabric Divina
(according to the customer order) Fibre composition: 100% wool
Colours: 0180, 0191, 0378, 0542, 0568, 0623, 0666, 0756, 0768,
0787, 0791, 0893, 0998



The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

CONDITIONS OF APPLICATION OF THE TEST REPORT:

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY: S. Aulehlová *Aulehlová*
CHECKED BY: O. Dolníčková *Dolníčková*
NUMBER OF PAGES: 3

**DATE OF
ACCEPTANCE:**
25.08.2026

**DATE OF
EXAMINATION:**
28.08. – 07.09.2026

**DATE OF
ISSUE:**
08.09.2026



+420 543 426 730
www.tzu.cz
azl@tzu.cz


Determination of colour fastness to rubbing

was tested according to ČSN EN ISO 105-X12

- rubbing conditions: dry / wet (wetting of rubbing cloth: 100 %)
- rubbing finger: for textiles [diameter (16±0,1) mm; downward force (9±0,2) N]
- climatic conditions during testing: temperature (20±2) °C, RH (65±2) %
- time of air-conditioning of samples: 4 hours

Result: grade of grey scale (staining to cotton rubbing cloth according to ČSN EN ISO 105-A03)


Sample description	Results	
Divina, colour 0180	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	3-4 / 3-4
Divina, colour 0191	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	2-3 / 2-3
Divina, colour 0378	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	4 / 4
Divina, colour 0542	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4 / 4
Divina, colour 0568	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4 / 4
Divina, colour 0623	staining in warp / weft direction	
	dry conditions	4-5 / 4-5
	wet conditions	2-3 / 2-3
Divina, colour 0666	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4-5 / 4-5
Divina, colour 0756	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4 / 4
Divina, colour 0768	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4-5 / 4-5





Sample description	Results	
Divina, colour 0787	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4-5 / 4
Divina, colour 0791	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4 / 3-4
Divina, colour 0893	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	4 / 4
Divina, colour 0998	staining in warp / weft direction	
	dry conditions	5 / 5
	wet conditions	3-4 / 3-4

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report





TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001
accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 26/1271

CUSTOMER: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

SAMPLE: Fabric Divina
(according to the customer order) Item: 1200
Fibre composition: 100% wool
Colours: 191, 623



The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

CONDITIONS OF APPLICATION OF THE TEST REPORT:

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY:
CHECKED BY:
NUMBER OF PAGES:

S. Aulehlová *Aulehlová*
O. Dolníčková *Dolníčková*
2

**DATE OF
ACCEPTANCE:**
16.10.2026

**DATE OF
EXAMINATION:**
16.10. – 19.10.2026

**DATE OF
ISSUE:**
19.10.2026



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Determination of colour fastness to rubbing


was tested according to ČSN EN ISO 105-X12

- rubbing conditions: dry / wet (wetting of rubbing cloth: 100 %)
- rubbing finger: for pile textile (19x24,5) mm; downward force (9±0,2) N
- climatic conditions during testing: temperature (20±2) °C, RH (65±2) %
- time of air-conditioning of samples: 4 hours

Result: grade of grey scale (staining to cotton rubbing cloth according to ČSN EN ISO 105-A03)

Sample	Results	
	staining in warp / weft direction	
Divina, colour 191	dry conditions	4-5 / 4-5
	wet conditions	3-4 / 3-4
	staining in warp / weft direction	
Divina, colour 623	dry conditions	4-5 / 4-5
	wet conditions	3 / 3
	staining in warp / weft direction	

Approved by:


Markéta Hrubanová
Head of Testing Laboratories

End of report

