

Müller-BBM GmbH
Robert-Koch-Strasse 11
82152 Planegg
Germany

Tel. +49 (89) 85602-0
Fax +49 (89) 85602-111

www.MuellerBBM.de

M. Eng. Philipp Meistring
Tel. +49(89)85602-228
Philipp.Meistring@MuellerBBM.de

2011-10-18
M60 836/81 msg/mol

Fabric Zulu Manufacturer Kvadrat A/S

**Determination of the
air flow resistance according to EN 29053**

Test Report No. M60 836/81

Client:	Kvadrat A/S Lundbergsvej 10 DK – 8400 Ebeltoft
Consultant:	M. Eng. Philipp Meistring Jan-Lieven Moll
Date of report:	2011-10-18
Date of delivery:	2011-10-03
Date of test:	2011-10-06
Total number of pages:	In total 6 pages: 4 pages text, 1 page Appendix A and 1 page Appendix B.

Table of contents

1	Task	3
2	Basics	3
3	Test object	3
4	Execution of measurements	3
5	Measurement results	4
6	Remarks	4

Appendix A: Measurement results and evaluation

Appendix B: List of test equipment

1 Task

On behalf of Kvadrat A/S, DK – 8400 Ebeltoft, the airflow resistance of the fabric type Zulu has to be measured according to EN 29053 [1].

2 Basics

This test report is based on the following documents:

- [1] EN 29053 “Acoustics – Materials for acoustical applications – Determination of airflow resistance”. 1993

3 Test object

The tested material is described by the manufacturer as follows:

- fabric type Zulu
- manufacturer Kvadrat A/S
- material: 100 % Trevira CS

The test laboratory has determined the following parameters:

- area specific mass $m'' = 98.1 \text{ g/m}^2$
- thickness $t = 0.36 \text{ mm}$

4 Execution of measurements

The airflow resistance was determined according to EN 29053 [1].

The measurements for the determination of the airflow resistance were carried out at different air velocities. The continuous airflow method was applied. The specimen holder has a diameter of 100 mm. The test specimen was fitted flat over the specimen holder, without stretching the material, sealed at the edges and fixed.

According to the standard the specific airflow resistance R_s is indicated as measurement result which was determined by extrapolation (linear regression) at an airflow velocity of $u = 0.0005 \text{ m/s}$.

The test equipment listed in Appendix B was used for the measurements.

5 Measurement results

For the tested fabric, type Zulu, a specific airflow resistance of $R_s = 3 \text{ Pa} \cdot \text{s/m}$ was determined.

For further information regarding the measurements, see Appendix A.

6 Remarks

The determined test results only refer to the prevailing conditions on the day of measurements.

This test report may only be published and copied as a whole including all of its appendixes. The publishing of extracts requires the prior written consent of Müller-BBM GmbH.



M. Eng. Philipp Meistring

MÜLLER-BBM
Accredited Testing Laboratory
according to DIN EN ISO/IEC 17025



EN 29053
Determination of Airflow Resistance

client: Kvadrat A/S
8400 Ebeltoft
Denmark


Projectnumber: M60836

Test Object: - fabric Zulu, manufacturer Kvadrat A/S
- material: 100 % Trevira CS

Specimen:
Diameter: 100 mm
Thickness: 0.36 mm
Area-related Mass: 98.1 g/m²

Barometric Pressure:
 $B = 95,0$ kPa
Temperature:
 $\theta = 27,0$ °C
Relative Humidity:
 $r. h. = 38,0$ %

$u/$ (mm/s)	$R_s/$ (Pa s/m)
1.22	2
0.65	3



Airflow Resistance $R_s = 3$ Pa s/m

Laboratory: Müller-BBM Planegg
Personnel: Moll
Date: 06.10.2011

mjars 1.0.0.2 - P:\msg\60\60836\MarsData\20111006\60836 Zulu.ms (18.10.2011)

List of test equipment

For the measurements and evaluations, the following test equipment was applied:

Name	Manufacturer	Type	Serial-No.
Digital Mass Flow Controller	Bronkhorst	E-201CV-5KO-RGD-33V	M8211608A
Digital Power Supply / Readout Systems	Bronkhorst	E-7100-13-01-01-RBB	M8211608B
Differential pressure transmitter with DSCM-A	Halstrup Walcher	P26	M8211704G
Software for data logging and evaluation	Müller-BBM	m ars	v1.0.0.2
Thermo-/Baro-/Hygrometer	Greisinger	GFTB 100	070806
Digital measuring slide	Mitutoyo	CD-15PPR	07019377
Electronic balance	Kern	440-49N	WC0633572