

# **Confidential Report**

Our Ref: 29/02870E/09/20







## Shirley Technologies Limited

Shirley Technologies Limited Wira House West Park Ring Road Leeds, LS16 6QL United Kingdom

Tel: +44 (0)113 259 1999

Web: http://www.shirleytech.com Email: info@shirleytech.co.uk

8 October 2020 Page 1 of 2

Our Ref: 29/02870E/09/20

Your Ref:

Client: Kvadrat A/S

Address: Lundbergsvej 10

8400 Ebeltoft Denmark

Job Title: Abrasion Resistance on One Sample

Client's Order Ref: --

Date of Receipt: 21 September 2020

Description of Sample(s): One part width sample of woven upholstery fabric, stated by the Client to be

34% polyester, 31% new wool, 26% acrylic, 4% cotton, 3% nylon, 2% linen

and referenced by the Client:-

Savanna

Work Requested: BS EN ISO 12947 – Martindale abrasion resistance

Note: this report relates only to the sample/s submitted and as described in this

report.







### Shirley **Technologies** Limited

**Shirley Technologies Limited** Wira House West Park Ring Road Leeds, LS16 6QL **United Kingdom** 

Tel: +44 (0)113 259 1999

Web: http://www.shirleytech.com Email: info@shirleytech.co.uk

8 October 2020 Page 2 of 2

Our Ref: 29/02870E/09/20

Your Ref:

Client: Kvadrat A/S

Testing atmosphere: Unless otherwise specified the sample(s) has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles (BS EN ISO 139:2005 + A1:2011) of 65±4% r.h. and 20±2°C.

#### Determination of the Abrasion Resistance of Fabrics by the Martindale Method - Part 2: Determination of Specimen Breakdown (ISO 12947-2: 2016)

Four specimens from the sample were tested, under a nominal pressure of 12 kPa(795±7g) in accordance with BS EN ISO 12947-2:2016, using a Martindale abrasion tester as described in BS EN ISO 12947-

Foam was not used to back the test specimens. Specimen breakdown (end point) was reached when two threads had completely broken. The change of shade of the test specimens was not assessed.

#### Individual results (number of rubs to end point)

≥50,000 45,000 ≥50,000 ≥50,000

Observations during testing: Some wearing of the chenille pile in localised areas at approx. 16,000 rubs

Result\*: 45.000

Type of fabric: Fabric made with chenille yarns

\* The quoted result is the lowest individual test result of all the test specimens tested

Reported by: L I Butler (Mrs)

LIBUTE J. Bullers Senior Laboratory Technician

J M Bullers (Mrs) Countersigned by:

Manager



