

Our Ref: SW/RM

5 November 2020

**Report 367842**

**Page 1 of 4**

Wooltex UK Limited  
 Woodland Mill  
 Dale Street  
 Longwood  
 Huddersfield, Yorkshire  
 HD3 4TG

Contact: Laura Franklin

DATE RECEIVED : 26 OCT 2020  
 QUALITY/REFERENCE : DIVINA MEL 180/ DIVINA MD 673/ DIVINA 793/  
 : DIVINA MEL 120/ CANVAS 746  
 REPUTED FIBRE CONTENT : DIVINA SAMPLING: 100% WOOL  
 : CANVAS SAMPLING: 90% WOOL, 10% NYLON  
 FABRIC DESCRIPTION : WOVEN  
 COLOUR/DESIGN : MULTI  
 ORDER NUMBER : 2783  
 PERFORMANCE STANDARD : GENERAL



**REPORT SUMMARY**

Tests	Method	Pass	Fail	Requirement
Colour fastness to light	BS EN ISO 105-B02:2014	Pass		Shade change grade 6
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion	Pass		60,000 Rubs
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion	Pass		60,000 Rubs
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion	Pass		60,000 Rubs
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion	Pass		60,000 Rubs



118 Lupton Avenue Leeds LS9 6ED  
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk  
 Registered No. 2899980 VAT No. 613 4310 86

5 November 2020

**Report 367842**

**Page 2 of 4**



**S. WISEMAN**  
**LABORATORY DIRECTOR**

*This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.*



118 Lupton Avenue Leeds LS9 6ED  
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk  
Registered No. 2899980 VAT No. 613 4310 86

**Report 367842**

**COLOUR FASTNESS TO:**

**BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6**

Canvas (746)

	Shade change	Requirement:
	6	Shade change grade 6

**PHYSICAL**

**BS EN ISO 12947-2:2016 Abrasion**

Divina Mel (180)

9 kPa load.

Number of rubs to breakdown:	Requirement:
Head 1 70,000	60,000 Rubs
Head 2 60,000	
Head 3 70,000	
Head 4 60,000	

**BS EN ISO 12947-2:2016 Abrasion**

Divina MD (673)

9 kPa load.

Number of rubs to breakdown:	Requirement:
Head 1 70,000	60,000 Rubs
Head 2 70,000	
Head 3 70,000	
Head 4 70,000	

**BS EN ISO 12947-2:2016 Abrasion**

Divina (793)

9 kPa load.

Number of rubs to breakdown:	Requirement:
Head 1 60,000	60,000 Rubs
Head 2 70,000	
Head 3 60,000	
Head 4 60,000	



**Report 367842**

**PHYSICAL**

**BS EN ISO 12947-2:2016 Abrasion**

Divina Mel (120)

9 kPa load.

Requirement:

60,000 Rubs

Number of rubs to breakdown:
Head 1 60,000
Head 2 60,000
Head 3 60,000
Head 4 60,000