

Received:07/08/2019	Completed:07/11/2019	Letter: R	JR	P.O.#:	Test Report #:	3-33385-0-
Client's Identification	Style: Loa. Composition: 100% Trevira CS. Weight: 180 gr/m ² . Product End Use: Roller Blind					
Tested For: Lone Henriksen			Key Test: NFPA 701-2019 TM#1			275
Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft Denmark			Tel: 011 45 89 53 18 66			Ext:
			Fax: 011 45 89 53 18 00			
LE:2019 V:01/19						
PC: 0.5H DL/jd						
TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2019 Edition - Test Method #1						
PRODUCT CONFIGURATION: <input checked="" type="checkbox"/> Single Layer; <input type="checkbox"/> Multi Layer						
RESULTS REPORTED: <input checked="" type="checkbox"/> Initially; <input type="checkbox"/> After 3 dry cleanings; <input type="checkbox"/> After 5 launderings @ 160°F						
RESULTS:						
Specimen #	Afterflame* (seconds)	Flamming Drip/Debris (seconds)	Weight Loss (percent)			
1	0	0	24.2			
2	0	0	27.7			
3	0	0	25.8			
4	0	0	22.7			
5	0	0	23.1			
6	0	0	19.4			
7	0	0	23.9			
8	0	0	22.4			
9	0	0	16.4			
10	0	0	14.9			
Mean:		0	Mean:	22.1		
STATISTICAL VALUES: SD = 4.0 3 SD = 12.0 Mean + 3 SD = 34.1						
ABBREVIATIONS USED: SD = Standard deviation. NT = Not tested.						
APPROXIMATE WEIGHT OF MATERIAL (as measured by SGS Govmark): 215 g/m ²						
PRECONDITIONING: <input checked="" type="checkbox"/> 0.5 hr @ 220°F (Standard) <input type="checkbox"/> 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)						
CONVERSION FACTOR: g/m ² ÷ 28.35 x .835 = oz/yd ²						
NOTE:						
1. All specimens prepared in the length direction.						
2. See addendum for individual specimen weights.						
(Page 1 of 2)						

Received:07/08/2019	Completed:07/11/2019	Letter: R	JR	P.O.#:	Test Report #:	3-33385-0-
Client's Identification	Style: Loa. Composition: 100% Trevira CS. Weight: 180 gr/m ² . Product End Use: Roller Blind					
Tested For: Lone Henriksen	Key Test: NFPA 701-2019 TM#1				275	
Kvadrat A/S						
Lundbergsvej 10	Tel: 011 45 89 53 18 66				Ext:	
8400 Ebeltoft Denmark	Fax: 011 45 89 53 18 00					

REMARKS:

- Flames did not project above the top of the specimen.
- Flames projected above the top of the specimen; Specimen #'s _____
- Other: _____

FAILURE CRITERIA: As cited by NFPA 701 - 2019 Edition Test Method #1


Afterflame	Flaming Drip/Debris (Mean)	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD

CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2019 Edition Test Method #1, the item tested:

- Passes; Fails; Requires testing of 10 additional specimens
 i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames could be cause for rejection by local fire authorities performing "match" field tests.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



Phyllis Pettit

JUL 18 2019

AUTHORIZED SIGNATURE
 SGS GOVMARK

/gb ijb



GOVMARK

Client Name : Kvadrat A/S
Addendum to Test Report #: 3-33385-0-R
Test : 701 TM1

<u>Specimen #</u>	<u>Weight Before Test (g)</u>	<u>Weight After Test (g)</u>	<u>Percent Weight Loss</u>
1	13.20	10.00	24.2
2	13.00	9.40	27.7
3	13.20	9.80	25.8
4	13.20	10.20	22.7
5	13.00	10.00	23.1
6	13.40	10.80	19.4
7	13.40	10.20	23.9
8	13.40	10.40	22.4
9	13.40	11.20	16.4
10	13.40	11.40	14.9

Mean Percent Weight Loss : 22.1
Standard Deviation : 4.0
3 x Standard Deviation : 12.0
Mean + 3 x Standard Deviation : 34.1