

kvadrat

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft Denmark
T +45 89 53 18 66 F +45 89 53 18 00
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

Fastness to light ISO 105-B02, method 2

Canvas 2

Colour number	Note
114	6
124	6
134	6
154	6
174	6
216	6
224	6
244	6
254	6
264	6
356	6
364	6
374	6
414	6
424	5
446	6
454	5
546	5-6
556	5-6
566	5-6
576	6
614	6
644	5-6
654	6
666	6
674	6
684	6
694	6
716	6
726	6
734	6

www.kvadrat.dk

746	6
764	6
786	6
794	6
836	6
854	6
926	6
936	6
946	6
954	6
964	6
974	6
984	6
996	6

Test reports

Highstreet 285108, 16. November 2016

Highstreet 353945, 27. November 2019

Highstreet 367842, 5. November 2020

Our Ref: SW/LS/JM

16 November 2016

Report 285108

Page 1 of 2

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

DATE RECEIVED	: 7 NOV 2016
QUALITY/REFERENCE	: CANVAS
REPUTED FIBRE CONTENT	: 90% WOOL, 10% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: MULTI
ORDER NUMBER	: 031116
PERFORMANCE STANDARD	: GENERAL

REQUEST: Colour fastness to light



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

16 November 2016

Report 285108

Page 2 of 2

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
716	6+
726	6+
786	6+
926	6
836	6
936	6
946	6
996	6

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
216	6+
356	6+
446	6+
546	5-6
556	5-6
566	5-6
576	6
666	6+

Our Ref: SW/LS/GL

27 November 2019

Report 353945

Page 1 of 5

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Laura Franklin

DATE RECEIVED	: 7 NOV 2019
QUALITY/REFERENCE	: CANVAS, STEELCUT TRIO
REPUTED FIBRE CONTENT	: CANVAS 90% WOOL, 10% NYLON
	: STEELCUT 92% WOOL 8% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: MULTI
ORDER NUMBER	: 2199
PERFORMANCE STANDARD	: GENERAL

REQUEST: Colour fastness to light



S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

Report 353945

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

Canvas

	Shade change
254	6
264	6+
364	6+
374	6+
414	6
424	5
454	5
614	6
644	5-6
654	6
674	6
684	6
694	6+
734	6
764	6+
794	6+
114	6+
124	6+
134	6+
154	6+

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

Canvas

	Shade change
174	6+
224	6+
244	6+
964	6
854	6+
954	6+
974	6+
984	6+

Report 367842

COLOUR FASTNESS TO:

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

Canvas (746)

	Shade change
	6

Requirement:
Shade change grade 6

PHYSICAL

BS EN ISO 12947-2:2016 Abrasion

Divina Mel (180)

9 kPa load.

Number of rubs to breakdown:
Head 1 70,000
Head 2 60,000
Head 3 70,000
Head 4 60,000

Requirement:
60,000 Rubs

BS EN ISO 12947-2:2016 Abrasion

Divina MD (673)

9 kPa load.

Number of rubs to breakdown:
Head 1 70,000
Head 2 70,000
Head 3 70,000
Head 4 70,000

Requirement:
60,000 Rubs

BS EN ISO 12947-2:2016 Abrasion

Divina (793)

9 kPa load.

Number of rubs to breakdown:
Head 1 60,000
Head 2 70,000
Head 3 60,000
Head 4 60,000

Requirement:
60,000 Rubs