

for the proof of fire behaviour according to DIN 4102-1



Prüfstelle für das
Brandverhalten
von Baustoffen
Dipl.-Ing. Uwe Kühnast

Steinstrasse 18
D - 14822 Borkheide
Fon: +49 33845 90901
Fax: +49 33845 90909
Mail: info@firelabs.de

PÜZ-Stelle (LBO): BRA09

Reference: FLT 3699719 (Translation of the German Prüfzeugnis - no guarantee for translation of technical terms)

Sponsor: Kinnasand GmbH
Danziger Str. 6
D - 26655 Westerstede

Order: 2019-07-24 **Arrived:** 2019-07-24

Description of samples: Uncoated fabric made of polyester to be used as curtain or for decorative purposes, named "Site".
(for details see page 2)

Delivered: 2019-07-25

Content of request: Proof of flammability to classify building materials to class B1 "schwerentflammbar" according to DIN 4102-1

Assessment: The examined product meets the requirements of class B1 for not easily flammable ("schwerentflammbare") building materials according to DIN 4102-1. If used in one layer, suspended freely or with distance of >40 mm to same or other plain materials.
(for details see page 5)

Validity: 2024-07-31

Sampling: The sample was sent to the laboratory by the sponsor.

Remark: If the above-mentioned building material is not used as product according to MBO § 2, there is no need for a general building supervisory test certificate.

This test certificate is not valid if the examined building material is used as product in the meaning of state building prescriptions (MBO § 17).

This test certificate does not replace an eventually necessary proof of applicability concerning building supervisory or building laws in the meaning of state building prescriptions.

This has to be verified by:

- "allgemeine bauaufsichtliche Zulassung" (general building inspectorate approval) or by
- "allgemeines bauaufsichtliches Prüfzeugnis" (general building inspectorate certificate) or by
- "Zustimmung im Einzelfall" (exceptional approval).

This test certificate can serve as a basis for building supervisory procedures for:

- regulated building products for the pre scribed proofs of conformity
- non-regulated building products for the needed proofs of applicability.

This test certificate comprises 5 pages and 2 appendices.

Approved testing, inspection and certification body

This test certificate must not be published and copied preceding agreement of the test laboratory and if agreed, only during validity and unchanged concerning appearance and contents. Agreement of the test laboratory has to be given in any case if norms in which the tests are based or other technical standards have changed.

TEST CERTIFICATE



1 Description of test material

1.1 Test material (according to the sponsor)

The material provided is an uncoated textile fabric of 34 % polyester yarn and 66 % flame retardant polyester yarn (referred to as 'polyester FR'). The fabric is intended to be used indoor as curtain or for decorative purposes and was named with the trade name "Site", article-no 6882 by the sponsor.

1.2 Description of the delivered samples

For the tests, a section of a fabric made of synthetic fibres with a length of approx. 2 m and a width of 3.05 m was sent to the laboratory.

The sample was marked with "6882 Site 0013" and batch KICUR124168.

Colour: light grey

Colour name: 0013, grey

Characteristic values: see paragraph 4.1; Photos: see enclosure 1

Further details are not known to the laboratory; a retain sample has been deposited..

2 Preparation of samples

For the small burner (Brennkasten) tests samples for edge flame exposure (dimensions 190 mm x 90 mm) and samples for surface flame exposure (dimensions 230 mm x 90 mm) have been cut in warp and in weft orientation of the fabric.

For the fire shaft (Brandschacht) tests 2 specimens were assembled. The samples (dimensions 1000 mm x 190 mm) for the test specimen A were cut in warp orientation; the samples for the test specimen B were cut in weft orientation of the fabric.

All samples were kept in a climate chamber acc. DIN 50014-23/50-2 until they reached constant weight.

3 Arrangement of samples

The tests in the fire shaft test ("Brandschacht") have been performed acc. DIN 4102-1 and -16 (building materials class B1). The small burner tests ("Brennkasten") have been performed acc. DIN 4102-1, chapter 6.2.5 (building materials class B2).

The tests were carried out in single layer, freely suspended.

Period of testing: August 2019

4 Results

- section 4.1 Material characteristics
- section 4.2.1 Test results class B2 ("Brennkasten")
- section 4.2.2 Test results class B1 ("Brandschacht")

4.1 Material characteristics


Table 1

Specific values		Specifications by manufacturer	Measured values	
			m.v.	s
Total thickness	[mm]	./.	0,37	0,010
Mass per unit area	[g/m ²]	135	114	

./. not received/not measured

m.v. mean value

s standard deviation



4.2 Results of the fire behaviour

4.2.1 Test results class B2 (Brennkasten)

All building materials class B1 must also meet the requirements of materials class B2 (flammable). The material, tested in "Brennkasten" acc. DIN 50 050 meets the requirements of building materials class B2; the material did not show burning particles/droplets during these tests. Exposing the flame to the front or reverse side did not influence the fire behaviour. (Results: see enclosure 2)

4.2.2 Test results class B1 (Brandschacht)

Table 3


Test results (part 1)						
line no.		Specimen				requirements
		A	B	C	D	
1	<u>Number of specimen arrangement</u> acc. DIN 4102 –15 Table 1	1	1	-	-	
2	<u>Maximal flame height</u> above bottom edge cm	30	30	-	-	*)
3	Time ¹⁾ min	1	1	-	-	
4	<u>Burning / melting through</u> Time ¹⁾min	1	1	-	-	
5	<u>Back side of the specimens:</u> <u>Flames / glowing</u> Time ¹⁾ min	./.	./.	-	-	
6	<u>Discolouring</u> Time ¹⁾ min	./.	./.	-	-	
7	<u>Falling of burning droplets</u> Begin ¹⁾ min	No	No	-	-	
8	Extend: Sporadic falling of burning droplets			-	-	
9	Continuous falling of burning droplets			-	-	
10	<u>Falling of burning parts</u> Begin ¹⁾ min	No	No	-	-	
11	Extend: Sporadic falling of burning parts					
12	Continuous falling of burning parts					
13	<u>Afterflame time at the bottom of the sieve (max.). min:s</u>	./.	./.	-	-	
14	<u>Impairment of the burner flames by dropping or falling Material</u> Time ¹⁾ min:s	No	No	-	-	
15	<u>Premature end of test</u> Final occurrence of burning at the specimen ¹⁾min	2	2	-	-	
16	Time of eventually end of test ¹⁾ min:s	./.	./.	-	-	

¹⁾ Indication of time: from the beginning of testing procedure

- Not tested

./. Not occurred

*) No cause for complaint



Test results (part 2)						
line no.		Specimen				requirements
		A	B	C	D	
17	<u>Afterflame after end of test</u> Timemin:s	No	No	-	-	
18	Number of specimen					
19	Front side of specimen					
20	Back side of specimen					
21	Flame lengthcm					
22	<u>Afterglow after end of test</u> Timemin:s	No	No	-	-	
23	Number of specimen					
24	<u>Place of appearance:</u> Lower half of specimen					
25	Upper half of specimen					
26	Front side of specimen					
27	Back side of specimen					
28	<u>Smoke density</u> ≤ 400 % min	0.9	0.5	-	-	
29	≥ 400 % min (very strong smoke density)	./.	./.	-	-	
30	Diagram fig. no.	1	3	-	-	
31	<u>Residual length</u> Individual valuecm	66 68 63 65	68 63 68 65	- - - -	- - - -	> 0
32	Average valuecm	65	66	-	-	≥ 15
33	Photo of test specimen fig. no.	2	4	-	-	
34	<u>Flue gas temperature</u> Maximum of average value...°C	112	113	-	-	≤ 200
35	Time ¹⁾min:s	9:38	9:40	-	-	
36	Diagram fig. no.	1	3	-	-	
37	Remarks: line 32: Due to the residual length of > 45 cm, no further tests were carried out (DIN 4102-16:2015-09, 5.2 b)).					

Specimen	Test-no.:	Direction of fabric
A	699719-001	warp
B	699719-002	weft

- 1) indication of time: from the beginning of testing procedure
- not tested
- ./. not occurred
- *) no cause for complaint



5 Assessment

According to the test results in section 4.2 the material, described in section 1 and 4.1, fulfils the requirements of building materials class B1 according to DIN 4102-1 if the material is used suspended freely or with a distance of > 40 mm to the same or other plain materials.

The requirements of building materials class B2 are also fulfilled. No falling of burning parts or droplets occurred during these tests.

The verification for

- outdoor usage (ageing by outdoor weathering)
- after washing or cleaning with chemicals

is not been proved with this test certificate.

6 Special remarks

This certificate is only valid for the material as described under paragraph 1. In combination with other materials or with additional coatings or surfaces etc. the burning behaviour may differ.

This test certificate is not valid, as soon as the product is used as a building product in the sense of the "Landesbauordnungen" (state building requirements, MBO § 17).

This test certificate is no substitute for a General Building Inspectorate Certificate. This test certificate is granted without prejudice to the rights of third parties, or particular private proprietary rights.

This test certificate can serve as a basis for building supervisory procedures for:

- regulated building products for the pre scribed proofs of conformity
- non-regulated building products for the needed proofs of applicability.

The explanations given in DIN 4102-1 app. D, especially concerning an external production control have to be considered.

This test certificate is valid until 2024-07-31, provided that the test methods, the classification rules and the technology do not change during this period.

Borkheide, 22nd of August 2019



Head of the test laboratory
(Dipl.-Ing. Uwe Kühnast)



This translation was issued the 22nd of August 2019, in a case of doubt the German version is valid solely.

Test specimen A




fig. 1
Graphs of the flue gas temperature and smoke density




fig. 2
View of test specimen after the test

Test specimen B




fig. 3
Graphs of the flue gas temperature and smoke density




fig. 4
View of test specimen after the test



Test results small burner test (Brennkasten)

Table 2

	warp direction*							weft direction*							dim.	requirements
	1	2	3	4	5	6	-	1	2	3	4	5	6	-		
Sample-No.	1	2	3	4	5	6	-	1	2	3	4	5	6	-	-	-
Ignition of the sample	1	1	1	1	1	2	-	1	1	1	1	1	2	1	s	-
Maximum flame height	3	3	2	3	2	1	-	2	2	3	2	2	2	3	cm	-
Time of the maximum	3	2	1	2	2	2	-	2	1	2	2	1	2	3	s	-
Flame tip reached the 150 mm mark	/.	/.	/.	/.	/.	/.	-	/.	/.	/.	/.	/.	/.	/.	s	≥ 20
Extinction of the flames	4	3	2	3	3	3	-	2	2	3	3	2	2	4	s	-
Ignition of filter paper	/.	/.	/.	/.	/.	/.	-	/.	/.	/.	/.	/.	/.	/.	s	1)
Smoke density (visual)	very low							very low							-	-
Afterburning time	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	s	-
Flames were extinguished after	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	/.	s	-
View of the samples after the test (20 seconds after exposure the flame): - in warp and weft direction destroyed length up to a max. height of 3 cm and a width of max. 2 cm, sintered and slightly sooty above.																

Samples 1-5: edge flame exposure

Samples 6: surface flame exposure

*) orientation of the samples during the tests

1) No ignition within 20 seconds

/.

Not occurred

dim. Dimension

Indication of time: from the beginning of testing procedure

Indication of measurements: from reference line of the flame