

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 15 September 2020

Our Ref: 23/57725-2

Your Ref: -

Page: 1 of 3

Client: Kvadrat A/S

Lundbergsvej 10 8400 Ebeltoft Denmark

Job Title: Testing of the Ignitability of Upholstered Fabric

Client's Order No:

Date of Receipt: 02 September 2020 Date of Test Start: 11 September 2020

Description of Sample(s): One sample of fabric identified as follows was received for testing:

Hallingdal 65, stated to be 70% new wool, 30% viscose

Work Requested: We were asked to make the following test:

Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered

seating by Smouldering and Flaming sources – Source 5 (Crib 5)





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 15 September 2020

Our Ref: 23/57725-2 Your Ref: -

Page: 2 of 3

### **Kvadrat A/S**

Sample was identified as follows:

Hallingdal 65, stated to be 70% new wool, 30% viscose

<u>Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)</u>

# **Pre-Treatment**

This material received no pre-treatment as stated to be inherently flame retardant.

#### Conditioning

The sample was conditioned and tested in the environments specified in Clause 10 of BS 5852: 2006 (2011).

### **Testing**

The material was tested according to BS 5852: 2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 19°C and 55 % relative humidity (R.H.).

# Foam Used

The sample was tested over combustion modified polyurethane foam with a density of approximately 36 kg/m<sup>3</sup>. The results for all tests are given in the table(s) on the following page(s).

Uncertainty of measurement has not been taken into account when presenting the test result. The overall uncertainty budget for both BS 5852: Part 1: 1979 is as follows:

Measurements: ± 2 mm
Timings: ± 2 seconds

Reported by:.....

B Bland

Laboratory Technician

Countersigned By:.....

P Doherty

Manager

Enquiries concerning this report should be addressed to Customer Services







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 15 September 2020

Our Ref: 23/57725-2 Your Ref: -

Page: 3 of 3

# **Kvadrat A/S**

# **RESULTS**

Sample Ref: Hallingdal 65, stated to be 70% new wool, 30% viscose

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1	Specimen 2
Time of Ignition (s)	23	39
Time of Flame Extinction (s)	246	248
Time of Smoke Extinction (s)	312	291
Time of cover split	DNS	DNS
Extent of damage (mm) - Seat		
Width	76	77
Length	94	100
Depth	26	27
Extent of damage (mm) - Back		
Width	346	358
Length	100	110
Depth	25	26
Melting	No	No
Dripping	No	No
Charring	Yes	Yes
Comments and Observations	DNS	DNS
Specimen Result (Ignition or Non-ignition)	Non-Ignition	Non-Ignition

# **Abbreviations**

ME – Manually extinguished EC – Escalating combustion

DNS – Material did not split DNO – Did not observe time of events

BTT – Burnt through thickness of foam BTE – Burnt to extremities

### Conclusion

The results indicate "Non-ignition" of the materials and the test is designated NI/5 i.e. Pass

Note: This report relates only to the samples submitted and as described in the report.

Uncertainty of measurement has not been taken into account when presenting the test result.

