

# Test Report

Report No.: A 888677-1



DANISH  
TECHNOLOGICAL  
INSTITUTE

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

**Assignor:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltøft  
Attn: Lone Henriksen

Page 1 of 2  
Initials  
Order no.: 888677  
No. of appendix: 1

**Subject:** Combination of upholstered material tested:  
**Cover:** Sample of fabric, designated: Parkland 231, Batch number GA23082-0401 (as per info from the assigner).  
Fibre composition: 100% Trevira CS (as per info from the assigner).  
Approximate mass per area unit: 439 g/m<sup>2</sup>.  
**Filling:** Flame-retardant polyurethane foam designated, CME38165.  
Approximate density: 35 kg/m<sup>3</sup>. (The foam is delivered by Danish Technological Institute).

**Sampling:** The test material was sampled by the client and received at the Danish Technological Institute 5 September 2019.

**Method:** BS 5852:2006 – Method of test for: Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources. Method of test for the ignitability of upholstery composites.  
Ignition source: Crib 5. Weight 17±1 g.

**Period:** The testing was completed 9 September 2019.

**Result:** Upholstery composite under test **meets (PASSES)** the requirements specified in BS 5852:2006, source 5, clause 4.

Details of the test are given on page 2 of this report.

**Storage:** The test material will be destroyed after 3 months, unless otherwise agreed.

**Terms:** The accredited test was carried out according to DANAK's general conditions see [www.danak.dk](http://www.danak.dk) and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

**Date/place:** 9 September 2019, Danish Technological Institute, Textile, Taastrup

**Signature:** Test responsible

Co-signatory



Report no.: A 888677-1  
Page: 2 of 2  
Initials: Chf/leln

**Results,  
continued:**

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

**Test result: Non-ignition > PASS**

	Test 1	Test 2
Duration of flames in min.	3:17 min.	4:03 min.
Smouldering ceased within 60 minutes	Yes	Yes
<b>Damage in the horizontal (seat) component:</b>		
- length in mm	43	42
- width in mm	41	35
- thickness in mm	51	48
<b>Damage in the vertical (back) component:</b>		
- width in mm	31	33
- thickness in mm	28	30

**Comments:**

Before testing the sample was **not** subjected to the water soaking and drying procedure described in BS 5852:2006, Annex E.

**Requirements:**

Criteria given in BS 5852:1982

- Progressive smouldering failure, clause 4.1.a, c, e and f are regarding crib 5
- a. Escalating combustion behaviour so that it is unsafe to continue the test and requires forcible extinction.
  - c. Smouldering until the specimen is essentially consumed or to the extremities of the specimen that is either the sides or to its full thickness, within the test duration (60 minutes).
  - e. Production of externally detectable amounts of smoke, heat or glowing 60 minutes after ignition of the crib.
  - f. On final examination: Evidence of charring other than discolouration, more than 100 mm in any direction, apart from upwards, from the nearest part of the original position of the source.

Flaming failure, clause 4.2.a, b, c, e and g are regarding crib 5

- a. Escalating combustion flaming behaviour so that it is unsafe to continue the test and requires forcible extinction.
- b. Burning until the specimen is essentially consumed within the test duration
- c. Flame front reaches either the sides or passes through the full thickness of the specimen within the duration of the test.
- e. Flaming for more than 10 minutes after ignition of the crib.
- g. Flaming debris causing an isolated floor fire that continues to flame longer than 10 minutes.

Report no.: A 888677-1  
Appendix: 1  
Page: 1 of 1  
Initials: Chf/leln

