

TEST CERTIFICATE

DATE SUBMITTED: 02-OCTOBER-2014
DATE ISSUED: 08-OCTOBER-2014
REPORT NO: 28869
COMPANY ORDER NUMBER: DB/mw.a/FTL-IFS.KAS.21410

CUSTOMER CONTACT NAMES: DONNA BARBER
TEL: 01502 575533
FAX: 01502 575533

COMPANY: FLAMENTEK LIMITED
RANNOCH HOUSE
HALL DRIVE
OULTON BROAD
LOWESTOFT
SUFFOLK
NR32 3PU

CUSTOMER SAMPLE DESCRIPTION

FIBRE COMPOSITION: 90% New Wool, 10% Nylon
SAMPLE NAME/REF: Canvas
SAMPLE COLOUR: Red
SAMPLE DESCRIPTION/QUALITY: Woven fabric, treated with a **Duraflam®** formulation by Fabric Flare Solutions Limited
END USE: Upholstery
FABRIC CUSTOMER: Kvadrat A/S
JOB REFERENCE: 21410 – KV0360.14 – Kvadrat A/S

FIRE TEST REQUESTED:

(Confidential Report)

BS 5852: 2006 Methods of test for (Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources) in accordance with Clause 11 using ignition source 5 Crib test


LAUNDERING PROCEDURE:

The sample was subjected to the water soaking procedure @ $40 \pm 1^{\circ}\text{C}$ as stated in BS 5852 2006 Annex E.

CONDITIONING PRIOR TO TESTING:

The sample was conditioned before the test for @ least 72 h in indoor ambient conditions and then immediately before the test for @ least 24 h at $23 \pm 2^{\circ}\text{C}$ and $50 \pm 5\%$ r h

Authorised signatures:

Signed:  v

Zeb Alam
Technical Manager

Please note: this test results issued on this certificate refer only to the item tested and therefore doesn't relate to the lot or batch of the product / sample. This test certificate shall not be duplicated.

Page 1 of 2

48B Halliwell Business Park, Rossini Street, Bolton, BL1 8DL
T: 01204 840086 F: 01204 840524 E: zeb@ifs-labs.com

TEST CERTIFICATE

DATE SUBMITTED: 02-OCTOBER-2014
 DATE ISSUED: 08-OCTOBER-2014
 REPORT NO: 28869
 COMPANY ORDER NUMBER: DB/mw.a/FTL-IFS.KAS.21410

UPHOLSTERY FILLING SOURCE 5:
 GRADE: CMHR35
 APPROX DENSITY: 35 kg per m³
 APPROX HARDNESS RANGE: 130 N

SIZE OF TEST RIG:
 BACK JUNCTION: 450+/-2 mm x 450+/-2 mm
 SEAT JUNCTION: 450+/-2 mm x 300+/-2 mm

TESTING ENCLOSURE AND ATMOSPHERE:
 The sample was tested in an atmosphere with a temperature of 10⁰ C to 30⁰ C and a relative humidity of 15% to 80%. The sample was tested in an enclosure with a volume greater than 20m³

PROCEDURE:
 The sample was mounted over the foam as described above, using the test rig as specified in BS 5852: 2006 Figure 4 & 5

REQUIREMENTS:
 Ignition Source: Crib 5
 Progressive Smouldering (maximum duration): 60 minutes after ignition of crib
 Flaming (maximum Duration): 10 minutes after ignition of crib

DATE OF TEST: 07-October-2014
 Fire test carried out by: Zeb Alam

RESULTS:

The following test results relate only to the ignitability of the combination of upholstery composites (BS 5852:2006 Clause 11) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

Observation of test:

Test No.	Ignition Source 5	Duration of	Special Features of Burning		Extent of damage to component					
					Vertical (mm)			Horizontal (mm)		
					Position	Flames (minutes)	Charring	Melting	Length	Width
1	M	04.29	Yes	Yes	98	51	20	61	58	17
2	M	05.03	Yes	Yes	109	63	24	72	65	19

LHS=Left Hand Side M= Middle RHS= Right Hand Side TOC= Top of Composite

COMMENTS & OBSERVATIONS:

The sample tested **complies with the flammability requirements** of BS 5852: 2006 (Clause 11 Upholstery Composite) Methods of test for (Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources) in accordance with Section 4 using ignition source 5 wooden crib test

Source 5 (crib): **PASS (P5)**