

Kvadrat A/S
Att.: Lone Henriksen
Lundbergsvej 10
DK-8400 Ebeltoft

Project no. A 1217488-25-1/103549
Page 1 of 2
Date 7 September 2004
Initials ntj/chf/ac


Gregersensvej
P.O. Box 141
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19


info@teknologisk.dk
www.teknologisk.dk

Test Report

- Material:** Sample of upholstery fabric collection in 18 colourways designated Coda.
Fibre content: 90% wool / 10% polyamide (customer's information)
- Sampling:** The test material was sent by the client and received at the Danish Technological Institute 12 July 2004.
- Method:** Colour fastness to artificial light, ISO 105-B02:1994, method 2.
Incl. AMD 1:1998 and AMD 2:2000
Normal conditions (1-8 scale, 8 best rating)
Test apparatus: Xenotest 450
- Period:** The testing was completed 6 September 2004.
- Results:** Results are given on page 2 of this report.
- Terms:** The test has been performed according to the rear side conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

7 September 2004, Danish Technological Institute, Textile


Naja Johansen
Signatory


Charlotte Fischer
Counter-signatory

Results:	<u>Designation – Coda</u>	<u>Colour fastness to artificial light</u>
	100	≥ 6-7
	130	6-7
	160	6
	191	6
	910	6
	107	≥ 6-7
	710	6
	197	6
	137	6-7
	700	5-6
	196	6
	660	6
	116	≥ 6-7
	610	6
	166	6
	103	6-7
	194	6
	410	6

Remark: The exposed test specimens are enclosed.



Test Report no. A 517176-1

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Kvadrat A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Coda	Received: 25-02-2013 Completed: 15-04-2013
Fibre content: 90% new wool, 10% polyamide (Manufacturer's information)	Sample no.: 517176-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	762 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	182 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	962 Colour fastness: 5
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	242 Colour fastness: 5

Test Report no. A 517176-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	232 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	382 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	722 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	222 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	410 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	442 Colour fastness: 5-6


Test Report no. A 517176-1

Test Methods	Results
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	422 Colour fastness: 7
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	642 Colour fastness: 6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	362 Colour fastness: 5-6
Colour fastness to artificial light ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	632 Colour fastness: 5-6


The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.44 of 2013-01-14.

15 April 2013, Danish Technological Institute, Textile


 Lea Larsen
 Ph. Direct: +45 72 20 21 36
 E-mail: lea.larsen@teknologisk.dk

Test responsible


 Signe Beck
 Ph. Direct: +45 72 20 21 46
 E-mail: sbks@teknologisk.dk

Co-reader