

## Investigation report

**SAHCO GmbH**  
Fr. Sarah Kemmerer  
Kreuzburger Str 17-19  
  
90471 Nürnberg

DELCOTEX  
Delius Techtex GmbH & Co. KG  
Vilsendorfer Str. 50  
33739 Bielefeld  
Germany

Homepage: [www.textillabor.eu](http://www.textillabor.eu)

Contact: Detlef von Seyfried  
Division: Laboratory/ Lab Manager  
Phone: +49 (0) 52 06 / 91 07 - 57  
Fax: +49 (0) 52 06 / 91 07 - 34

Date: 05.12.2018

### Investigation report No. 18-E-626

order description: **Abrasion resistance DIN EN ISO 12947-2 (2017-03)**  
**Determination of fabric propensity to surface fuzzing and to pilling - Part 2:**  
**Modified Martindale method ISO 12945 (2000-11)**  
**Seam slippage resistance DIN EN ISO 13936-2 (2004-07) method B**  
**according to Martindale method (specimen breakdown) DIN EN 14465(2006-09)**

sample: 600177 Base 2777  
sampling: by orderer  
orderer: see address  
date of order: 21.09.2018  
date of delivery: 22.10.2018  
date of testing: 30.11.2018  
number of pages: 4

#### Remark:

The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see [www.textillabor.eu](http://www.textillabor.eu)).



## Investigation report No. 18-E-626

page 4 of 4

### Instructions for performing

5. **Method: Seam slippage resistance DIN EN ISO 13936-2 (2004-07) method B according to Martindale method (specimen breakdown) to DIN EN 14465 (2006-09)**
6. **Measuring conditions:**

Type: furnishing fabric  
Tensile force: 180 N

### Test results

**Article: 600177 Base 2777**

	Seam opening [mm]
Warp direction (seamline weft direction)	3,34
Weft direction (seamline warp direction)	4,64

**Remark:** According to to DIN EN 14465 (2006-09) in reference to pilling tendencies of furnishing fabrics, the article is ranked within **category B**.



i. A. Detlef von Seyfried  
Labor/Laborleitung  
DELCOTEX Delius Techtex GmbH & Co. KG

Als verbindlich gelten nur die Angaben im unterzeichneten Prüfbericht.