

Investigation report

SAHCO GmbH
Fr. Sarah Kemmerer
Kreuzburger Str 17-19

90471 Nürnberg

DELCOTEX
Delius Techtex GmbH & Co. KG
Vilsendorfer Str. 50
33739 Bielefeld
Germany

Homepage: www.textillabor.eu

Contact: Detlef von Seyfried
Division: Laboratory/Manager
Phone: +49 (0) 52 06 / 91 07 - 57
Fax: +49 (0) 52 06 / 91 07 - 34

Date: 14.03.2019

Investigation report No. 19/889

order description: Colour fastness to artificial light: Xenon arc fading lamp
DIN EN ISO 105-B02 (2014-11)
according to DIN EN 14465 (2006-09) Specification Upholstery fabric
Pilling test according to DIN EN ISO 12945-2 (2000-11)
according to DIN EN 14465 (2006-09) Specification Upholstery fabric
Seam slippage resistance DIN EN ISO 13936-2 (2004-07)
Textiles - Determination of the abrasion resistance of fabrics by the Martindale
method - Part 2: Determination of specimen breakdown DIN EN ISO 12947-
2:2017-03

sample: 600112 Flint, colour 001 to 20, 70% Viscose, 30% Leinen

sampling: by orderer

orderer: see address

date of order: 20.02.2019

date of delivery: 25.02.2019

date of testing: 11.04.2019

number of pages: 5

Remark:

The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).



Investigation report No. 19/889

page 3 of 5

Instructions for performing

**3. Method: Seam slippage resistance DIN EN ISO 13936-2 (2004-07)
in according to DIN EN 14465 (2006-09) Specification Upholstery fabric**

4. Measuring conditions

Type: furnishing fabric
Tensile force: 180 N

Test results

Article: 600112 Flint, colour 001

	Seam opening [mm]
Warp direction (seamline weft direction)	3,3 (3,0 – 3,5)
Weft direction (seamline warp direction)	3,2 (3,0 – 3,5)

Remark: According to DIN EN 14465 (2006-09) the article, in reference to seam slippage resistance in furnishing fabrics, the article is ranked within **category A**.