

# Test Report

Report No.: A 862639-2



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

**Assignor:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltøft  
Attn.: Lone Henriksen

Page 1 of 1  
Chf/leln  
Order no.: 862639  
No. of appendices: 1

**Subject:** Upholstery fabric Phlox, 90% new wool, 10% polyester. (as per info from the assigner).



**Sampling:** The test material was sampled by the client and received at the Danish Technological Institute 12.03.2019.

**Method:** See Appendix 1.

**Period:** The testing was completed 15.03.2019.

**Result:** Individual results appear from Appendix 1.

**Storage:** The test material will be destroyed after 6 months, unless otherwise agreed.

**Terms:** Accredited testing was carried out in compliance with international requirements (EN/ISO/IEC 17025:2005) and in compliance with Danish Technological Institute's General Terms and Conditions regarding Commissioned Work accepted by Danish Technological Institute. The test results apply to the tested products only. This report may be quoted in extract only if the laboratory has granted its written consent.

**Date/place:** 18.03.2019, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

**Signature:** Test responsible

Co-signatory



Report no.: A 862639-2  
 Appendix: 1  
 Page: 1 of 1  
 Initials: Chf/leln

| <b>Test Methods</b>  | <b>Results</b>  |                        |                     |                        |                     |
|--|---|------------------------|---------------------|------------------------|---------------------|
| <p><b>Determination of the slippage resistance of yarns at a seam in woven fabrics - Fixed load method</b><br/>           DS/EN ISO 13936-2:2004<br/>           Performed on: Standard seam<br/>           Load: 180 N<br/>           Test conditions: 21°C, 65%RH</p> | <p>Average of 5 determinations</p> <table> <tr> <td>Seam parallel to warp:</td> <td>2,0 mm seam opening</td> </tr> <tr> <td>Seam parallel to weft:</td> <td>1,5 mm seam opening</td> </tr> </table> | Seam parallel to warp: | 2,0 mm seam opening | Seam parallel to weft: | 1,5 mm seam opening |
| Seam parallel to warp:   | 2,0 mm seam opening   |                        |                     |                        |                     |
| Seam parallel to weft:   | 1,5 mm seam opening   |                        |                     |                        |                     |