

Test Report

Report No.: A 862639-1



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Assignor: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltøft
Attn.: Lone Henriksen

Page 1 of 1
Chf/Ieln
Order no.: 862639
No. of appendices: 1

Subject: Upholstery fabric Atom, 90% new wool, 8% nylon, 2% polyester. (as per info from the assigner).



Sampling: The test material was sampled by the client and received at the Danish Technological Institute 12.03.2019.

Method: See Appendix 1.

Period: The testing was completed 15.03.2019.

Result: Individual results appear from Appendix 1.

Storage: The test material will be destroyed after 6 months, unless otherwise agreed.

Terms: Accredited testing was carried out in compliance with international requirements (EN/ISO/IEC 17025:2005) and in compliance with Danish Technological Institute's General Terms and Conditions regarding Commissioned Work accepted by Danish Technological Institute. The test results apply to the tested products only. This report may be quoted in extract only if the laboratory has granted its written consent.

Date/place: 18.03.2019, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

Signature: Test responsible

Co-signatory



Report no.: A 862639-1
 Appendix: 1
 Page: 1 of 1
 Initials: Chf/leln

| Test Methods | Results | | | | |
|--|---|------------------------|---------------------|------------------------|---------------------|
| <p>Determination of the slippage resistance of yarns at a seam in woven fabrics - Fixed load method DS/EN ISO 13936-2:2004 Performed on: Standard seam Load: 180 N Test conditions: 21°C, 65%RH</p> | <p>Average of 5 determinations</p> <table> <tr> <td>Seam parallel to warp:</td> <td>2,5 mm seam opening</td> </tr> <tr> <td>Seam parallel to weft:</td> <td>1,5 mm seam opening</td> </tr> </table> | Seam parallel to warp: | 2,5 mm seam opening | Seam parallel to weft: | 1,5 mm seam opening |
| Seam parallel to warp: | 2,5 mm seam opening | | | | |
| Seam parallel to weft: | 1,5 mm seam opening | | | | |