

Our Ref: SW/LS/RM

23 December 2016

Report 288079

Page 1 of 3

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

DATE RECEIVED	: 16 DEC 2016	RAAS	LILA
QUALITY/REFERENCE	: FAT SNAKE TR1659, FAT SNAKE TR1663		
REPUTED FIBRE CONTENT	: NOT GIVEN		
FABRIC DESCRIPTION	: WOVEN		
COLOUR/DESIGN	: GREEN/BLUE		
ORDER NUMBER	: 121216		
PERFORMANCE STANDARD	: GENERAL		

REQUEST: Resistance to pilling & abrasion and seam slippage



S. WISEMAN
LABORATORY DIRECTOR



L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86



23 December 2016

Report 288079

Page 2 of 3

PHYSICAL

BS EN ISO 13936-2:2004 Seam Slippage

TR1659 **RAAS**

	Length	Width
Seam opening at 180 N	5.7 mm	2.2 mm

BS EN ISO 13936-2:2004 Seam Slippage

TR1663 **LILA**

	Length	Width
Seam opening at 180 N	3.5 mm	3.5 mm

BS EN ISO 12945-2:2000 PILLING MODIFIED MARTINDALE

TR1659

Revs	Grade
500	4-5
1000	4
2000	4
3000	4
5000	4

Sample tested: As Received

Sample tested against Wool abradant as specified in BS EN ISO 12947.

BS EN ISO 12945-2:2000 PILLING MODIFIED MARTINDALE

TR1663

Revs	Grade
500	4
1000	3-4
2000	3-4
5000	3-4

Sample tested: As Received

Sample tested against Wool abradant as specified in BS EN ISO 12947.

23 December 2016

Report 288079

Page 3 of 3

PHYSICAL

BS EN ISO 12947:1998 Abrasion

TR1659. 12 kPa Load

Head 1 60,000+
Head 2 60,000+
Head 3 60,000+
Head 4 60,000+

BS EN ISO 12947:1998 Abrasion

TR1663. 12 kPa Load

Head 1 60,000+
Head 2 60,000+
Head 3 60,000+
Head 4 60,000+