

Test Report

Report No.: A 907468-1



DANISH
TECHNOLOGICAL
INSTITUTE


Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Assignor: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Attn.: Lone Henriksen

Page 1 of 1
Chf/leln
Order no.: 907468
No. of appendices: 1

Subject: Upholstery fabric Helia, fibre composition: 47% new wool, 32% acrylic, 15% viscose, 4% nylon, 2%polyester. (as per info from the assigner).



Sampling: The test material was sampled by the client and received at the Danish Technological Institute 18.12.2019

Method: See Appendix 1.

Period: The testing was completed 20.12.2019

Result: Individual results appear from Appendix 1.

Storage: The test material will be destroyed after 6 months, unless otherwise agreed.

Terms: The accredited test was carried out according to DANAK's general conditions see www.danak.dk and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

Date/place: 20.12.2019, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

Signature: Test responsible

Co-signatory



Report no.: A 907468-1
 Appendix: 1
 Page: 1 of 1
 Initials: Chf/leln

Test Methods	Results
<p>Determination of the slippage resistance of yarns at a seam in woven fabrics - Fixed load method DS/EN ISO 13936-2:2004 Performed on: Standard seam Load: 180 N Test conditions: 21°C, 65%RH</p>	<p>Average of 5 determinations Seam parallel to warp: 1,0 mm seam opening Seam parallel to weft: 2,0 mm seam opening</p>