

Our Ref: SW/MG/JM

5 September 2016

Report 280801

Page 1 of 2

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Sharon Daniel

DATE RECEIVED	: 30 AUG 2016
QUALITY/REFERENCE	: TR1617 (EX TR1637) TWILL WEAVE
REPUTED FIBRE CONTENT	: 92% WOOL, 8% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: GREY STRIPE
ORDER NUMBER	: 260816
PERFORMANCE STANDARD	: GENERAL

REQUEST: Pilling, seam slippage, abrasion



S. WISEMAN
LABORATORY DIRECTOR



M. GRAINGER
SENIOR TECHNOLOGIST

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

5 September 2016

Report 280801

Page 2 of 2

PHYSICAL

BS EN ISO 13936-2:2004 SEAM SLIPPAGE

	Length	Width
Seam opening at 180 N	2.5 mm	1.7 mm

BS EN ISO 12945-2:2000 PILLING MODIFIED MARTINDALE

Revs	Grade
500	3-4
1000	3-4
2000	3-4
5000	3-4

Sample tested: As Received

BS EN ISO 12947:1998 ABRASION

Load 12 kPa

Head 1 60,000+
Head 2 60,000+
Head 3 60,000+
Head 4 60,000+



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

